

INDEX

ALUMINUM IN STEEL 7

BORON 3

CALCIUM IN STEEL 7
CARBON STEEL 3, 4
CAST IRON 20, 21, 22, 23, 24

GRAPHITIC CARBON 20

HIGH ALLOY STEEL 19
HIGH NICKEL STEEL 15

IRON 2

LOW ALLOY STEEL 5, 6, 7, 8, 9, 10
LOW NICKEL STAINLESS STEEL 16

MANGANESE STEEL 15
MARAGING STEEL 15
MILD STEEL 7, 8

NICKEL BINARY 7
NITROGEN IN STEEL 7

POWDER 2, 17, 19, 25

RARE EARTHS 21
RESULFURIZED STEEL 11

SILICON STEEL 11, 12
SOLUBLE BORON 3
STAINLESS STEEL 16, 17, 18

TOOL STEEL 13, 14

IRON CHIPS AND POWDER

= class, where 1 = CRM and 2 = RM analysis listed in mass %

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	N	Al	Co	Mo	Nb	O	Sn	Ti	V	W	
1	NCS HC15014	0.0208	0.246	0.0121	0.007	0.0922	0.020	0.0202	0.013	.	0.046	0.0012	.	.	.	
1	SRM 2165	(0.0063)	0.144	0.0052	0.003643	(0.0040)	0.0013	0.155	0.050	.	(0.0060)	0.0012	0.0055	0.0004	.	0.002	0.0051	0.0040	.	
1	VS S1/3	0.0036	0.0023	0.0012	0.0034	0.0099	0.0033	0.0042	0.0064	0.027	0.018	0.0006	0.00029	.	.	0.00023	.	.	.	
1	VS S1/2	0.0036	0.0010	0.0014	0.0042	0.0088	0.0093	0.0047	0.0016	0.0129	0.0074	0.0007	0.0003	.	.	0.00028	.	.	.	
1	IARM 27G	(0.003)	(0.003)	(0.003)	0.0011	(0.07)	0.040	0.045	0.043	(0.0003)	(0.0013)	(0.0009)	(0.002)	(0.002)	0.025	(0.001)	<0.005	(0.001)	<0.005	
1	NCS HC11011b	0.0023	0.013	0.0014	0.0014	0.0023	0.0045	0.0027	0.0066	0.0045	<(0.0001)	0.0012	0.00030	(0.00004)	.	0.00015	<(0.0001)	<(0.0001)	(0.00004)	
1	NCS HC15002g	0.0013	0.00018	(0.0001)	0.0010	0.0014	0.00024	0.0052	0.00019	.	0.00065	(0.0001)	0.0033	.	Cd:(0.0001)	(0.0001)	(0.0001)	(0.0001)	(0.0001)	
1	Y TSC101	0.0013	0.00018	(0.0001)	0.0010	0.0014	0.00024	0.0052	0.00019	.	0.00065	(0.0001)	0.0033	.	Cd:(0.0001)	(0.0001)	(0.0001)	(0.0001)	(0.0001)	
1	ECRM 088-2	0.0006	0.0809	0.0048	0.0070	0.0052	0.0163	0.0275	0.0244	.	.	0.0061	0.00029	.	
1	JSS 003-8	0.00040	0.00109	0.00040	0.00016	0.00064	0.00039	0.00007	0.00012	0.00068	0.00667	0.000046	0.000020	0.000048	.	0.000020	<0.00006	(0.000006)	(0.00001)	
1	JSS 003-7	0.00034	0.00054	0.00038	0.00016	0.00052	0.00032	0.00007	0.00013	0.00061	0.00682	0.000047	0.000017	<0.0002	.	0.000017	<0.00006	trace	trace	
1	SRM 937	99.90% Fe
1	ECRM 097-2C	.	0.012	0.00538	0.00181	0.00285	0.00793	0.0241	0.0213	0.00294	.	0.0139	0.00370	.	.	0.00043	.	0.00011	0.00386	

analysis listed in mg/kg except

Number	Ag	As	B	Bi	Ca	Mg	Pb	Sb	Se	Ta	Te	Zn	Zr	Units
NCS HC15014	.	2	0.85	5	100 g chips
SRM 2165	2	10	9.44	<1	.	<1	3	10	150 g chips
VS S1/3	.	2.6	1.0	2.6	.	100 g chips
VS S1/2	.	3	1.0	2.7	.	100 g chips
IARM 27G	.	(16)	(6)	<70	(2)	(2)	(20)	<100	.	<200	.	<50	(30)	100 g chips
NCS HC11011b	.	26	2.3	<0.1	3	.	(0.2)	2.9	<0.1	<0.1	<0.1	1.5	<0.1	50 g chips also trace Cd, Ce, Hf, La, and Mg
NCS HC15002g	.	(1)	.	(1)	17	2.2	(1)	(1)	.	.	.	(1)	.	15 g powder Fe > 99.984%
Y TSC101	.	(1)	.	(1)	17	2.2	(1)	(1)	.	.	.	(1)	.	15 g powder Fe > 99.984%
ECRM 088-2	7.2	100 g chips
JSS 003-8	.	(0.1)	(0.26)	<0.7	<1	<1	0.04	<2	<1	<0.7	<1	(0.2)	<0.5	150 g chips also trace Cd, Ce, and La
JSS 003-7	.	<1	0.18	<0.7	<1	<1	(0.02)	<2	<1	<0.7	<1	(0.2)	<0.5	150 g chips
SRM 937	50 g chips
ECRM 097-2C	.	28.1	1.2	1.2	.	1.5	.	1.4	.	100 g chips

There are also purity iron powders in our Geological catalog, Iron Ore section <http://www.brammerstandard.com/pdf/geological.pdf>

CRM IRON CHIPS AND POWDER

analysis listed in mass %

Number	C	Mn	P	S	Si	Cu	Ni	Cr	N	Al	Ins.Al	As	B	Co	Mo	Ti	Units
NCS HC15007	0.091	0.399	0.0246	0.017	0.341	0.201	0.243	0.148	.	0.180	100 g chips
NCS HC15007a	0.080	0.358	0.036	0.031	0.506	0.254	0.203	0.170	0.018	0.432	50 g chips
NCS HC15006	0.080	0.043	0.0159	0.0075	0.171	0.135	0.147	0.043	.	0.088	100 g chips
NCS HC15017	0.061	0.319	0.04	0.005	0.166	0.02	0.02	0.022	0.0146	0.284	50 g chips
NCS HC15006a	0.061	0.254	0.021	0.0058	0.341	0.168	0.182	0.114	0.012	0.412	50 g chips
BAM 031-3	0.055	0.329	0.014	0.021	0.037	0.020	.	.	0.0050	0.054	.	0.013	100 g chips
BAM 031-2	0.0344	0.296	0.053	(0.052)	.	0.083	.	.	0.012	.	.	0.061	100 g chips
NCS HC15005a	0.030	0.106	0.0061	0.025	0.182	0.123	0.162	0.147	0.011	0.205	50 g chips
ECRM 083-1	0.028	0.289	0.0077	0.0100	.	0.016	0.014	.	0.00189	100 g chips
NCS HC15004	0.0272	0.246	0.0094	0.012	0.0994	0.031	0.0202	0.013	.	0.37	100 g chips
NCS HC15004a	0.027	0.195	0.014	0.0063	0.018	0.089	0.116	0.048	0.016	0.290	50 g chips
NCS HC41002	0.023	0.178	0.016	0.009	0.075	0.309	0.003	150 g chips
NCS HC15016	0.022	0.201	0.0072	0.0027	0.199	0.066	0.066	0.032	0.0123	0.217	50 g chips
NCS HC15015	0.017	0.151	0.01	0.0022	0.214	0.118	0.105	0.017	0.0064	0.413	50 g chips
NCS HC15003a	0.012	0.034	0.0019	0.020	0.017	0.021	0.030	0.016	0.015	0.060	50 g chips
NCS HC13013	0.0041	0.126	0.0085	0.021	0.018	150 g powder
IPT 73	0.0034	0.044	0.0034	0.0049	0.0028	0.076	0.033	0.030	0.0076	0.004	.	TEMPORARILY UNAVAILABLE	

Number	C	Mn	P	S	Si	Cu	Ni	Cr	N	Al	Ins.Al	As	B	Co	Mo	Ti	Units
--------	---	----	---	---	----	----	----	----	---	----	--------	----	---	----	----	----	-------

CRM		CARBON STEEL CHIPS WITH NITROGEN										analysis listed in mass %										JSS: 150 g units					all others: 100 g units				
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	N	Nb	Ti	V	W	As	B	Ca	Co	O	Pb	Sn	Zr								
ECRM 090-1C *	1.054	0.226	0.013	0.0095	0.281	.	0.053	0.121	.	0.009	0.0146	0.00043	.	0.204	0.00239	.	.							
VS U7/9	1.02	0.255	0.0080	0.0158	0.156	.	0.102	0.123	.	.	0.0094	(0.01)								
JSS 066-6	0.837	0.852	0.0146	0.00356	0.245	0.0102	.	.	0.0218	.	0.00318								
JSS 066-5	0.835	0.853	0.0145	0.0035	0.244	0.0106	.	.	0.0218	.	0.0031	last								
VS UNL4/3	0.736	0.851	0.0200	0.028	0.220	0.037	0.055	0.023	.	.	0.0041	0.127								
VS UNL4/4	0.734	0.853	0.0200	0.0268	0.221	0.037	0.055	0.023	.	.	0.0041	0.123								
DSZU CX05	0.703	0.558	0.0200	0.0270	0.302	0.037	0.026	0.054	(0.005)	(0.004)	0.0051	.	(0.003)	(0.004)	(0.002)	(0.003)	.	.	(0.002)	.	(0.0002)	(0.002)	250 g								
VS U23	0.665	0.560	0.0197	0.0277	0.300	0.038	0.024	0.055	.	.	0.0050								
JSS 061-9	0.633	0.490	0.0100	0.00502	0.245	0.0238	.	.	0.0302	.	0.00387								
JSS 061-8	0.630	0.484	0.0099	0.0050	0.243	0.0238	.	.	0.030	.	0.0037	last								
IARM 373A	0.63	0.70	0.0123	0.031	0.22	0.107	0.048	0.096	0.002	0.0176	0.0088	0.001	0.0017	0.023	(0.002)	0.0046	0.0003	0.0005	0.005	0.002	(0.001)	0.0069	(0.003)								
JSS 057-10	0.580	0.800	0.0150	0.0161	0.184	0.0139	.	.	0.034	.	0.0049								
VS U24	0.563	0.611	0.0129	0.0214	0.334	0.0129	0.0138	0.059	.	.	0.0079								
DSZU CX04	0.559	0.607	0.0133	0.0216	0.327	0.0147	(0.017)	0.0573	(0.004)	.	0.0079	.	(0.002)	(0.005)	.	(0.002)	(0.0001)	(0.0009)	250 g								
JSS 057-9	0.529	0.759	0.0164	0.0199	0.182	0.0128	.	.	0.0272	.	0.0052	last								
IARMF1050-18	0.499	0.79	0.0045	0.027	0.223	0.179	0.068	0.100	(0.003)	0.018	0.0097	(0.0013)	0.0008	0.0270	.	(0.0030)	(0.0005)	.	0.0056	0.0026	.	0.0103	.								
IARM 200C	0.453	0.775	0.007	0.020	0.241	0.236	0.094	0.100	0.002	0.023	0.0079	0.0014	0.0011	0.025	(0.002)	0.006	0.0003	0.0020	0.007	0.0037	.	0.0090	(0.004)								
TH 1020	0.449	(0.63)	0.0306	0.0332	(0.27)	(0.01)	(0.03)	(0.04)	(0.04T)	(0.01)	0.0063	Sol.Al: 0.0347								
IARM 210D	0.412	0.73	0.0052	0.030	0.230	0.273	0.122	0.096	(0.002)	0.034	0.011	0.001	0.0104	0.024	(0.002)	0.0059	0.0004	0.0009	0.007	0.0034	0.001	0.010	(0.001)								
JSS 050-8	0.410	0.762	0.0119	0.00278	0.207	0.0118	.	.	0.0307	.	0.00442	Sol.Al: 0.0295	(0.002)	.	(0.0001)	(0.0009)							
IARM 349A	0.41	1.49	0.011	0.025	0.192	0.300	0.178	0.189	0.0020	0.059	0.0100	0.0012	0.0013	0.027	0.004	0.005	0.0003	0.0015	0.0085	0.003	(0.001)	0.015	(0.002)								
JSS 050-6	0.38	0.50	0.013	0.0057	0.19	0.008	.	.	0.023	.	0.0029	last								
JSS 050-7	0.378	0.498	0.0129	0.0058	0.190	0.0075	.	.	0.0233T	.	0.0028	Sol.Al: 0.0224	last								
VS S7/6	0.355	0.702	0.0201	0.0169	0.327	0.032	0.039	0.034	0.0086	.	0.0047	Sol.Al: 0.0074								
IARM 360A	0.331	0.733	0.008	0.023	0.260	0.235	0.078	0.113	0.0016	0.024	0.0102	0.0015	0.0010	0.039	(0.001)	0.0060	0.0004	0.0017	0.0067	0.004	(0.001)	0.010	(0.001)								
IARM 209D	0.322	0.68	0.0084	0.021	0.268	0.243	0.079	0.137	(0.003)	0.037	0.0107	0.0014	0.0011	0.042	(0.002)	0.0060	0.0002	0.002	0.007	0.005	0.001	0.012	.								
BCS 434/2	0.275	1.54	0.061	0.0141	0.51	.	.	.	0.037	0.238	0.0104	0.038								
IARM 359A	0.267	0.686	0.0094	0.020	0.233	0.186	0.068	0.121	0.002	0.023	0.0094	0.002	0.0009	0.027	(0.001)	0.0073	0.0003	0.0013	0.0069	0.0044	(0.001)	0.0100	(0.001)								
IARMF1020-18	0.226	0.547	0.006	0.024	0.235	0.198	0.078	0.125	(0.003)	0.0252	0.0098	(0.0012)	.	0.036	.	0.0044	.	(0.002)	0.0065	(0.007)	.	0.0080	.								
IARM 213C	0.201	0.922	0.007	0.025	0.25	0.149	0.068	0.099	0.0019	0.022	0.0116	0.0011	0.0010	0.035	(0.002)	0.0058	0.0003	0.0014	0.0074	0.0042	0.0011	0.0081	(0.0004)								
IMZ 1.18/5	0.20	1.43	0.023	0.030	0.44	0.11	0.077	0.073	0.098	.	0.0051	Sol.Al: 0.091								
JSS 030-9	0.195	0.750	0.0237	0.0076	0.237	0.0239	.	.	0.0227	.	0.00312	Sol.Al: 0.0218	last								
IARM 28B	0.18	0.75	0.010	0.029	0.23	0.36	0.13	0.13	0.003	0.029	0.0094	0.002	0.002	0.002	(<0.001)	0.008	0.0002	.	0.011	0.0070	(<0.01)	0.014	.								
IARM 28D	0.1700	0.80	0.010	0.016	0.27	0.11	0.090	0.081	0.0110	0.025	0.0079	0.002	0.001	0.019	(0.003)	0.0039	0.0002	.	0.009	0.006	.	0.008	.								
IARM 28E	0.169	0.68	0.009	0.0026	0.171	0.120	0.145	0.079	0.011	0.033	0.0088	0.001	0.001	0.019	0.002	0.007	0.0001	.	0.008	0.0052	<0.001	0.010	.								
JSS 023-10	0.1255	0.675	0.0135	0.00345	0.201	0.0111	.	.	0.0420	.	0.00311	Sol.Al: 0.0413								
VS U1/12	0.109	0.541	0.0217	0.0249	0.214	0.063	0.056	0.045	.	.	0.0072								
VS UNL3/4	0.105	0.897	0.101	0.130	0.221	0.135	0.096	0.076	.	.	0.0038	(0.005)								
VS U1/11	0.101	0.578	0.0233	0.0267	0.218	0.064	0.067	0.049	.	.	0.0076								
GBW 01407a	0.080	0.358	0.036	0.031	0.506	0.254	0.203	0.170	0.432	.	0.018								
GBW 01406a	0.061	0.254	0.021	0.0058	0.341	0.168	0.182	0.114	0.412	.	0.012								
ECRM 057-2C	0.0507	0.246	0.0120	0.0127	.	0.0146	0.0096	0.0114	0.059	.	0.0023								
ECRM 083-2C	0.0315	0.2160	0.0106	0.00561	0.00747	0.0127	0.0116	0.0219	0.0784	.	0.00157	0.00177	.	.	.	0.00236	.	.	0.00439								
GBW 01405a	0.030	0.106	0.0061	0.025	0.182	0.123	0.162	0.147	0.205	.	0.011								
DSZU CX01	0.029	0.086	0.0063	0.0085	0.146	0.209	0.147	0.222	(0.014)	(0.031)	0.0160	.	(0.003)	(0.003)	(0.007)	(0.01)	(0.0002)	.	(0.011)	.	(0.009)	(0.012)	200 g								
GBW 01404a	0.027	0.195	0.014	0.0063	0.180	0.089	0.116	0.048	0.290	.	0.016								
BCS 111	0.0258	0.155	0.0033	0.0054	0.0253	0.0171	0.0387	0.0197	0.0348	0.0008	0.0034	(0.0005)	0.0004	0.0009	.	0.0021	.	.	.	0.0144	.	0.0015	.								
BCS 431/2	0.0249	0.902	0.121	0.0065	0.015	.	0.040	0.049	.	.	0.0052	0.0040								
IMZ 1.7/4	0.017	0.13	0.013	0.032	(0.005)	0.016	0.012	0.004	0.0040	0.0017	0.0044	Sb: 0.001	0.001	0.001	0.0005	0.0045	0.001	Sol.Al: 0.0022	Zn: 0.001	0.0005	0.0021	.	.								
VS U18/1	0.0122	0.130	0.0038	0.0089	0.036	0.018	0.0163	0.026	.	.	0.0145								
VS UNL1/2	0.012	0.131	0.0036	0.0091	0.033	0.019	0.16	0.026	(0.001)	.	0.0151	0.0028								
GBW 01403a	0.012	0.034	0.0019	0.020	0.017	0.021	0.030	0.016	0.060	.	0.015								
VS S2/5	0.0077	0.028	0.0032	0.0054	0.046	0.069	0.072	0.047	0.319	.	0.0070	0.0026								
SS 111/1	0.0070	0.1623	0.0045	0.0049	0.0039	0.0089	0.0161	0.0055	.	0.0005	0.0025	0.0004	0.0002	.	0.0011	.	.	0.0006	.								
BCS 432/2	0.0065	0.712	0.017	0.0																											

CRM	LOW ALLOY STEEL CHIPS WITH NITROGEN																				IPT 96: 120 g	JK, JSS, NCS, SRM: 150 g	all others: 100 g
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn	Other
IARM 324A	0.99	1.01	0.009	0.028	0.163	0.22	0.081	0.42	0.002	.	0.007	0.022	0.0082	0.014	0.0016	0.0017 (0.003)	0.006	0.0004	0.003	.	.	0.011	Ca: 0.0009
BCS 401/2	0.935	1.19	0.026	0.0078	0.60	0.101	0.019	0.138	0.074	.	0.0042	0.49	0.0159	.	.	0.496
IMZ C-119	0.93	1.15	0.018	0.006	0.16	0.042	0.049	0.062	0.010	0.007	.	.	0.0086	.	(0.0007)	0.006	Ca: (0.0002)
BAM 036-1	0.858	0.327	0.0074	0.0095	0.194	0.065	(0.058)	(0.091)	(0.015)	.	.	.	0.010	.	.	(0.019)	.	0.0233
ECRM 182-1	0.790	0.389	0.0076	0.011	0.368	0.141	0.152	0.591	0.020	.	.	.	0.0102	.	.	0.1770	.	0.0202
JK 3B	0.742	0.803	0.0101	0.0071	0.251	0.0175	0.0591	0.0529	0.0036	.	0.0048	0.0051	0.0054	.	.	(0.002)	0.0044	.
ECRM 059-2C	0.721	0.495	0.0046	0.0084	0.188	0.0074	0.0198	0.0090	0.00045	0.00020	.	0.0018	0.0051
IPT 29A	0.614	0.565	0.012	0.0076	0.372	0.012	0.794	0.845	.	0.028	.	0.276	0.0039	.	.	0.080
IMZ C-120	0.60	0.40	(0.049)	0.026	0.34	0.10	0.085	0.20	0.033	.	.	.	0.0115	0.065	.	.	0.077	0.008	Sb: 0.031
ECRM 079-2	0.596	0.743	0.0233	0.192	0.247	0.046	0.022	0.0379	0.021	.	.	.	0.0074	0.004	.	.	.	0.0037	.
IARM 321A	0.53	1.53	0.012	0.017	0.65	0.212	0.47	0.24	0.004	last	0.007	0.026	0.0100	0.0017	0.0036	0.089	0.0050	0.0052	0.0008	(0.005)	(0.001)	0.019	Ca: 0.0016
ECRM 055-2C	0.5199	0.687	0.0102	0.0205	0.3094	0.2089	0.3121	0.3217	.	.	0.0257	0.0960	0.01069	.	0.00104	0.00245	0.0166	0.0187	.	.	.	0.0162	Sb: 0.00376
ECRM 091-1	0.518	0.310	0.312	.	.	.	0.098	0.0111
IARM 299A	0.469	0.70	0.008	0.002	0.22	0.100	0.57	1.03	0.092	.	0.0054	0.99	0.0028	0.006	0.0038	0.120	0.010	0.003	0.0003	(0.002)	(0.001)	0.0055	.
BAM 030-4	0.456	0.603	0.018	0.021	0.318	0.061	0.042	0.117	0.042	.	.	.	0.0051	0.012	.	.	.	0.0055	.
ECRM 080-1	0.452	1.116	0.028	0.024	0.317	.	.	0.025	0.0073	(0.006)	last
IARM 30H	0.425	0.937	0.015	0.022	0.253	0.131	0.063	0.97	0.020	.	0.0071	0.199	0.0081	(0.003)	(0.0024)	(0.0040)	(0.007)	0.0046	(0.0007)	(0.0016)	(0.0005)	0.008	Sb: 0.0013
IARM 305B	0.425	0.58	0.011	0.014	0.349	0.214	0.156	1.63	0.92	.	0.007	0.32	0.0044	0.002	0.0044	0.004	(0.004)	(0.006)	0.0006	0.0006	(0.0003)	0.011	Ca: 0.0007
IARM 252D	0.423	0.842	0.0075	0.0128	0.256	0.270	0.424	0.468	0.024	.	0.0078	0.204	0.0068	0.0013	0.0012	0.0022	(0.004)	0.0053	(0.0002)	(0.0013)	(0.0004)	0.012	Sb: 0.0024
IARM 252C	0.416	0.92	0.025	0.008	0.248	0.109	0.505	0.501	0.017	.	0.008	0.205	0.0083	0.002	0.001	0.005	<0.005	0.004	(0.0001)	(0.002)	0.001	0.007	last
IARM 252E	0.413	0.87	(0.009)	(0.012)	0.257	0.164	0.407	0.486	0.028	.	0.0093	0.204	0.0064	.	0.0010	(0.0028)	.	0.0046	.	.	.	0.0075	.
SRM 12h	0.407	0.842	0.018	0.027	0.235	0.073	0.032	0.074	.	.	.	0.006	0.006	.	.	0.003
IARM 252F	0.406	0.88	0.011	0.009	0.247	0.182	0.412	0.463	0.026	.	0.0086	0.210	0.0059	0.0016	0.0010	(0.003)	(0.003)	(0.006)	.	.	.	0.006	.
SRM 139b	0.403	0.778	0.013	0.019	0.242	0.097	0.510	0.488	.	.	.	0.182	0.007	.	.	(0.004)
IARM 31G	0.40	0.689	0.0136	(0.013)	0.262	0.183	1.814	0.820	0.0214	.	0.0083	0.223	0.0069	(0.0023)	0.0015	0.0036	(0.004)	(0.004)	0.0004	.	.	0.0077	.
SRM 100b	0.397	1.89	0.023	0.028	0.210	0.064	0.030	0.063	.	.	.	0.237	0.004	.	.	0.003
JSS 502-7	0.396	0.759	0.0187	0.0106	0.248	0.150	0.110	1.048	0.0234	0.0222	.	0.218	0.0079	.	.	0.0056
IARM 31F	0.39	0.70	0.012	0.018	0.258	0.181	1.78	0.83	0.026	last	0.008	0.204	0.0058	(0.002)	0.0017	0.0028	(0.005)	(0.005)	0.0003	(0.001)	(0.001)	0.015	Ca: 0.0005
IARM 322A	0.317	1.40	0.009	0.021	0.42	0.33	0.28	0.159	0.002	Sb: 0.0027	0.006	0.021	0.023	(0.001)	0.0016	0.124	0.003	0.005	0.0009	0.006	(0.001)	0.016	Ca: 0.0019
IARM 143F	0.308	0.573	(0.011)	0.0177	0.23	0.221	0.088	0.865	0.026	.	0.010	0.163	0.0098	(0.0015)	(0.0012)	0.0046	(0.003)	0.0051	.	(0.003)	.	0.010	.
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn	Other
IPT 142	0.304	0.801	0.022	0.025	0.242	0.226	0.421	0.505	0.029	0.027	0.008	0.179	0.0133	0.020	(0.006)
BAM 032-2	0.271	0.556	0.0129	0.0254	0.282	0.085	(0.040)	(0.088)	0.0044	0.020
ECRM 017-1	0.261	0.725	0.015	0.022	0.266	0.062	0.085	0.044	0.0091
IARM 195B	0.255	1.84	0.018	0.005	1.16	0.52	1.00	0.216	0.029	.	0.101	0.052	0.0070	0.007	0.002	0.082	0.38	0.021	0.0039	0.0017	0.002	0.084	last
ECRM 197-1C	0.219	0.792	0.0073	0.0232	0.275	0.152	0.148	0.451	0.0313	.	0.0135	0.402	0.0114	.	0.0005	.	.	0.0083	.	.	.	0.0097	.
IARM 182B	0.21	0.81	0.016	0.037	0.27	0.017	0.47	0.49	0.038	.	0.006	0.172	0.0040	(0.003)	(0.003)	0.004	(0.01)	(0.003)	(0.0003)	(0.003)	0.19	0.0019	.
ECRM 187-2C	0.2038	1.257	0.0066	0.0300	0.2111	0.1288	0.1755	1.132	0.0223	.	0.0112	0.0623	0.0105	.	.	0.0122	.	0.0057	0.00048	.	.	0.0237	.
JSS 514-8	0.201	0.836	0.0166	0.0188	0.186	0.0120	0.0282	1.20	0.031	.	.	0.265	0.0096	.	.	0.0059	last
ECRM 192-1C	0.1875	1.377	0.0029	0.0010	0.219	0.0453	0.755	0.0717	0.0306	0.0285	0.0055	0.482	0.0118
JK 21	0.1741	1.46	0.0148	0.011	0.36	0.045	0.035	0.024	0.005*	0.032	0.008	0.004	0.008	0.0175	0.0008	0.002	*	= Insoluble Aluminum	.	.	.	0.006	.
IMZ C-195	0.17	1.18	0.010	0.0008	0.29	0.11	0.18	1.04	(0.017)	.	.	0.076	0.0061	.	(0.012)	(0.005)
ECRM 194-2C	0.1694	1.282	0.0137	0.00049	0.2974	0.0313	0.3316	0.760	0.0669	.	0.00328	0.402	0.00319	0.0290	0.00322	0.00161	.	0.00208	0.00155
ECRM 194-1C	0.1532	1.188	0.0097	0.00059	0.431	0.0751	0.3417	0.733	0.0837	.	.	0.2857	0.0115	.	.	0.0243	.	0.0042	0.0020	.	.	.	Ca: 0.0026
VS UNL17	0.139	0.436	0.0205	0.0189	0.394	0.299	0.378	0.725	0.0043
ECRM 060-1	0.122	0.45	(0.024)	(0.031)	(0.17)	(0.060)	(0.039)	(0.028)	(0.004)	.	.	(0.0005)	0.0040	(0.005)
VS UNL5/3	0.115	1.36	0.0053	0.0035	0.484	.	.	.	0.021	.	.	.	0.0194	0.066	.	0.085
IPT 96	0.109	0.845	0.017	0.0049	0.286	0.272	0.018	0.614	.	0.041	0.0048	.	0.0092	0.0072
BAM 042-1	0.108	0.666	0.007	0.024	0.037	0.041	0.029	0.016	0.010	.	.	.	0.0078	0.054
IMZ C-169	0.099	0.54	0.015	0.0155	0.35	0.128	0.073	2.20	0.075	.	0.012	1.03	0.0193	(0.0045)	0.001	(0.016)	(0.001)	0.062	.
IARM 37C	0.096	0.408	0.014	(0.004)	0.31	0.121	0.148	4.34	(0.010)	.	0.015	0.500	0.008	(0.004)	(0.0025)	0.017	(0.012)	(0.009)	.	.	.	0.009	.
VS UNL10/3	0.095	0.678	0.027	0.022	0.961	0.447	0.636	0.750	0.0111	.	.	0.0080	0.0063	.	.	0.0077	.	(0.003)
DSZU CX02a	0.092	2.12	0.022	0.0164	0.86	0.016	0.014	0.028	(0.004)	.	(0.003)	(0.00											

CRM MILD STEEL CHIPS WITH NITROGEN

analysis listed in mass % except * which is mg/kg

JK, other JSS, NILAB: 150 g all others: 100 g

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn	Zr*
BCS 402/2	1.311	0.228	0.0161	0.0138	0.111	0.302	0.808	0.652	0.161	.	.	0.140	0.0069	.	.	0.194
ECRM 035-2C	1.277	0.305	0.0038	0.011	0.216	0.0085	0.0190	0.0104	0.0193	.	.	0.0056	0.0230	.	0.0030	.	.	0.0017
JK 20A	1.263	.	.	0.0094	0.0027	.	.	0.161	1.75	.	.	.	0.160	.	.
ECRM 195-1C	0.756	0.571	0.017	0.012	0.467	0.036	0.33	1.56	.	.	.	0.77	0.010	.	.	0.31
SS 115	0.6224	0.682	0.0123	0.00093	0.2078	.	0.0196	0.0198	0.0527	.	.	.	0.0067	.	0.0027	.	.	Ca:0.0058
SS 116	0.617	0.6756	0.0092	0.00176	0.201	.	0.0155	0.0141	0.0587	.	.	.	0.0069	.	0.00171	.	.	Ca:0.0036	.	.	0.00012	.	.
ECRM 179-2C	0.598	0.539	0.027	.	0.578	0.111	0.0741	1.081	.	.	.	0.070	0.0068	0.00144	.	0.188	1.87	.	.	.	0.00013	.	.
BAM 130-1	0.546	1.593	0.0209	0.0158	0.313	0.072	(0.031)	(0.032)	0.0038	.	.	.	0.0093	.	.	(0.003)	.	0.0167
IARM 34C	0.50	0.739	0.0090	0.0011	0.30	0.078	0.085	0.914	0.068	.	0.005	0.022	0.0030	0.004	0.0045	0.206	(0.003)	0.0024	0.0003	0.0008	(0.0003)	0.0058	.
IPT 100	0.462	0.755	0.016	0.019	0.188	0.053	0.524	1.08	.	0.029	(0.006)	0.94	0.0075	.	(0.0012)	0.117
BCS 114	0.403	0.416	0.0044	0.0046	0.295	0.358	1.502	0.187	0.078	.	0.0171	0.184	0.0043	0.0042	0.0096	0.0086	.	0.0025	0.0008	.	.	0.041	51
BCS 112	0.394	0.436	0.0043	0.0026	0.289	0.149	1.461	1.236	0.0148	.	0.0175	0.190	0.0024	0.0065	0.0100	.	.	0.0021	0.0007	.	.	0.0086	.
ECRM 129-3C	0.3684	0.371	0.0110	0.0165	0.2087	0.0804	1.022	1.702	1.016	.	0.0148	0.206	0.0046	.	0.0030	.	.	0.0049	.	.	Sb:0.00059	0.0067	(30)
JK 7B	0.342	0.697	0.0057	0.0064	0.267	0.021	1.34	1.34	0.014	0.010	.	0.182	0.0050	.	.	0.004
BCS 222/1	0.3095	0.618	0.0175	0.0089	0.227	0.150	3.536	0.0535	.	.	0.0379	0.0287	0.0100
JSS 501-7	0.299	0.780	0.0202	0.0106	0.249	0.147	0.1014	1.047	0.024	0.023	.	0.216	0.0087	.	0.0104
IARM 229B	0.220	0.858	0.0073	0.0106	0.329	0.0153	0.030	0.017	0.025	.	0.0116	0.495	0.0072	(0.0019)	0.0019	0.0059	(0.003)	(0.002)	(0.0006)	(0.0017)	(0.0005)	0.0012	(8)
IARM 33D	0.209	0.593	0.009	0.023	0.207	0.072	1.78	0.139	0.026	.	0.008	0.229	0.0053	0.002	0.003	0.002	<0.005	0.0035	0.0002	0.0013	<0.001	0.005	.
JSS 517-7	0.200	0.826	0.0107	0.0084	0.250	0.0132	3.04	1.75	(0.006)	.	.	0.516	0.0061	.	.	(0.003)	last
ECRM 180-1	0.197	1.286	0.0174	0.0249	0.362	0.115	0.096	1.250	0.0068	0.030
ECRM 187-1C	0.195	1.354	0.014	0.025	0.026	0.161	0.096	1.186	0.046	.	0.014	.	0.014	0.018	0.0004	.	.	0.011	.
IPT 97	0.165	1.11	0.015	0.026	0.231	0.129	0.227	1.22	.	0.028	0.012	0.064	0.0119	0.023	0.002	0.024	.	.	0.0022
ECRM 193-1C	0.14	0.97	0.007	0.009	0.40	0.60	1.18	0.18	0.025	.	0.007	0.35	0.0108	0.0232	(0.0013)	(0.002)	.	0.0062
IARM 36C	0.14	0.49	0.009	0.014	0.25	0.142	0.085	2.43	(0.017)	.	(0.008)	0.98	0.008	.	.	0.0061	.	(0.005)	.	.	.	(0.008)	.
IARM 35B	0.13	0.45	0.006	0.015	0.58	0.11	0.084	1.12	0.016	.	0.008	0.46	0.0079	0.003	0.003	0.005	(0.001)	0.006	0.0005	0.0016	(0.001)	0.006	.
IARM 35L	0.119	0.535	0.007	0.014	0.679	0.123	0.071	1.35	0.017	.	0.0070	0.607	0.0072	(0.0026)	(0.0015)	0.0037	(0.004)	0.0045	0.00044	.	.	0.0088	.
IARM 35C	0.115	0.44	0.012	0.014	0.56	0.271	0.102	1.09	0.029	.	0.011	0.52	0.0093	0.002	0.003	0.005	(0.005)	(0.005)	0.0004	0.0016	(0.001)	0.017	.
CMSI 1105	0.035	1.79	0.089	0.009	0.59	0.46	0.020	1.03	0.59	last

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn	Zr*
--------	---	----	---	---	----	----	----	----	----	-----	----	----	---	----	----	---	---	----	---	---	----	----	-----

CRM ELEMENTS in STEEL

Number	Al	Ca	N	Units
IMZ C-133	.	.	0.0360	100 g
IMZ C-131	0.0043	.	0.0333	100 g
IMZ C-135	0.0274	0.0008	0.0238	100 g
IMZ C-141	0.0071	.	0.0154	100 g
IMZ C-130	0.0046	0.0024	0.0153	100 g
IMZ C-139	(0.029)	0.0031	0.0113	100 g
IMZ C-132	0.0021	0.0002	0.0097	100 g
IMZ C-137	0.0017	0.00025	0.0083	100 g
IMZ C-140	0.0307	0.0015	0.0083	100 g
SS 116	0.0587	0.0036	0.0069	100 g
BCS 115	0.0527	0.0058	0.0067	100 g
IMZ C-138	0.0022	.	0.0063	100 g
IMZ C-134	0.0124	0.0005	.	100 g
IMZ C-136	0.0034	0.00031	.	100 g

CRM IRON/NICKEL BINARY CHIPS

typical analysis listed in mass % 50 g

Number	Ni	C	Mn	P	S	Si	Cu	Cr	Al	Co	N
C14X FeNi500	50.09	0.0488	0.115	0.0259	0.243	0.203	0.105	0.093	0.052	0.499	.
C14X FeNi450	45.20	0.0045	0.0149	0.0416	0.038	0.567	0.078	0.048	0.552	0.654	.
C14X FeNi250	25.10	0.0084	0.0121	0.011	0.58	0.019	0.035	0.0334	0.103	0.746	.
C14X FeNi200	20.06	0.0137	0.0284	0.010	0.0089	1.12	0.074	0.102	0.018	0.994	.
C14X FeNi100	10.12	0.095	0.272	0.015	0.027	0.061	0.029	0.070	0.025	.	0.0055
C14X FeNi80	8.10	0.097	0.330	0.015	0.029	0.097	0.030	0.250	0.029	.	0.0061
C14X FeNi60	6.08	0.100	0.330	0.0155	0.028	0.075	0.028	0.073	0.025	.	0.0055

CRM MILD STEEL CHIPS, chart 1 of 2

analysis listed in mass % except * which is mg/kg

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	W	As	B	Nb	Pb	Sb	Sn	Units	
VS S18/4	1.42	0.199	0.0180	0.0122	0.241	0.142	0.193	0.555	0.262	4.55	100 g	
ECRM 188-1	1.094	.	.	0.0113	.	.	(0.28)	1.538	.	.	(0.06)	(0.17)	.	(0.02)	100 g	
SRM 2161	(1.02)	0.680	0.0407	0.0347	0.1816	0.2973	1.999	0.2195	0.0539	Zr:0.0132	0.0256	0.1030	0.180	0.0540	(<0.005)	0.0131	21.5*	197.8*	(0.1*)	0.00548	0.0474	150 g	
NCS HC21201b	0.990	0.315	0.0065	0.0054	0.239	0.086	0.042	1.47	0.037	0.035	0.0093	0.032	0.0035	.	.	0.0092	.	.	0.00017	0.0045	0.020	100 g	
CMSI 1101	0.91	2.09	0.054	0.030	0.056	0.20	0.076	0.10	.	0.015	100 g	
BAM 126-1	0.841	1.817	0.0092	0.0050	(0.241)	(0.098)	(0.038)	0.317	0.143	100 g	
BCS 403/2	0.750	1.677	0.055	0.0381	0.209	0.221	0.223	0.463	0.0485	.	.	0.088	.	0.341	100 g	
VS UNL12/4	0.736	0.360	0.0070	0.0034	0.276	0.387	0.316	0.794	.	.	.	0.200	.	0.685	100 g	
CMSI 1103	0.70	0.28	0.083	0.064	0.041	0.12	0.93	1.45	(0.0007)	100 g	
IRSID 113-1	0.680	0.586	(0.013)	(0.006)	0.249	0.146	1.744	0.816	.	.	.	0.413	100 g	
SRM 363	0.62	1.50	0.029	0.0068	0.74	0.10	0.30	1.31	0.24	Ca:2.2*	0.048	0.028	0.050	0.31	0.046	0.010	13.10*	0.049	0.00186	(0.002)	0.104	150 g	
NCS HC28212	0.506	0.664	0.014	0.022	0.304	0.208	0.109	1.04	0.0049	0.002	0.014	0.016	0.0021	0.154	100 g	
IPT 31	0.497	0.794	0.021	0.009	0.146	0.251	0.106	1.15	.	0.087	.	.	.	0.250	100 g	
BCS 407/2	0.490	0.195	0.038	0.0105	0.66	0.397	0.527	3.03	0.040	.	.	0.83	.	0.19	100 g	
CMSI 1183	0.476	0.675	0.0201	0.016	0.273	0.203	0.62	0.125	150 g	
BCS 407/1	0.47	0.047	0.030	0.010	0.59	0.57	0.59	2.95	.	.	.	0.78	.	0.18	100 g	
CMSI 1156	0.467	0.687	0.025	0.022	0.472	.	1.515	1.03	0.147	0.69	150 g	
VS UNL16/1	0.440	0.660	0.028	0.031	0.266	0.044	0.041	0.925	100 g	
ECRM 082-1	0.415	0.769	0.013	0.030	0.235	0.025	0.027	0.018	0.149	.	.	100 g	
IPT 17A	0.415	0.724	0.014	0.021	0.260	0.074	0.820	.	.	.	0.039	0.259	100 g	
VS UNL16	0.409	0.750	0.020	0.0237	0.300	0.082	0.049	0.958	100 g	
CMSI 1125	0.409	0.742	0.015	0.011	0.376	0.086	0.063	1.053	.	.	.	0.0088	.	0.0023	100 g	
SRM 32e	0.4086	0.7983	0.00888	0.0210	0.2775	0.1266	1.1938	0.6775	.	.	.	0.0228	.	(0.00225)	150 g	
IRSID 107-1	0.407	0.611	.	.	0.286	0.108	0.191	1.443	0.345	.	.	0.323	(0.011)	100 g	
IPT 25	0.400	0.902	0.012	0.007	0.222	0.040	0.072	1.01	.	.	.	0.280	100 g	
VS UNL14/3	0.400	0.369	0.0078	0.0040	0.545	0.193	0.169	1.72	0.78	0.182	0.313	100 g	
ECRM 155-1	0.40	0.56	0.019	0.012	0.23	(0.17)	1.43	1.08	(0.01)	.	.	0.34	.	(<0.01)	100 g	
ECRM 190-1C	0.395	1.28	0.0112	0.0044	0.278	.	0.934	2.18	.	.	0.034	0.410	100 g	
VS UNL15/4	0.392	0.668	0.0056	0.0051	0.338	.	0.713	2.07	.	.	.	0.205	.	.	0.66	0.0078	0.0041	.	.	.	100 g		
CMSI 1153	0.39	4.25	0.0246	0.011	0.335	0.275	0.238	1.44	0.93	.	.	0.17	150 g	
ECRM 152-1	0.39	1.61	0.032	0.043	0.18	0.21	0.15	0.09	.	.	.	0.26	.	(<0.01)	100 g	
IRSID 102-1	0.389	0.367	0.012	(0.006)	0.281	0.169	4.40	0.261	.	.	.	1.20	100 g	
IRSID 108-1	0.384	0.690	0.0176	0.017	0.340	0.118	0.215	2.92	.	.	.	0.538	100 g	
SRM 361	0.383	0.66	0.014	0.0143	0.222	0.042	2.00	0.694	(0.021)Ca:1.0*	.	0.032	0.19	0.020	0.011	0.017	0.017	4.78*	0.022	0.000025	0.0042	0.010	150 g	
VS UNL19	0.382	0.864	0.0179	0.0207	0.238	0.154	0.703	0.741	100 g	
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	W	As	B	Nb	Pb	Sb	Sn	Units	
CMSI 1155	0.375	0.691	0.026	0.032	0.345	0.164	0.26	0.999	150 g
CMSI 1154	0.367	0.56	0.018	0.027	0.375	.	3.95	0.957	.	.	.	0.143	150 g	
GBW 01334a	0.358	0.573	0.014	0.0086	0.272	0.150	0.020	1.03	.	0.061	.	0.137	100 g	
VS S21/5	0.333	0.278	0.0110	0.0059	0.281	0.183	0.193	2.65	.	.	.	0.755	.	0.71	4.93	(0.007)	.	0.067	.	.	.	100 g	
IRSID 023-1	0.331	0.667	0.021	0.016	0.264	0.280	.	.	100 g	
CMSI 1152	0.33	1.02	0.032	0.024	0.40	0.17	0.26	0.18	.	.	.	1.37	.	0.25	0.50	.	0.034	150 g	
ECRM 153-1	0.315	0.81	0.011	0.027	0.079	0.088	2.55	0.66	(0.003)	.	.	0.58	100 g	
IPT 36	0.315	0.430	0.016	0.004	0.291	0.129	0.217	1.25	.	0.86	.	0.201	100 g	
ECRM 154-1	(0.3)	(0.6)	(0.02)	(0.009)	(0.2)	(0.1)	3.54	(0.05)	.	.	(0.04)	(0.03)	100 g	
BCS 408/1	0.285	0.51	0.037	0.028	0.2 3	0.66	4.45	0.102	.	.	.	0.09	.	0.031	last	
BCS 408	0.28	0.64	0.043	0.030	0.24	0.73	4.58	0.090	.	.	.	0.14	.	0.19	100 g	
JSS 152-18	0.277	0.440	0.0174	0.0056	0.387	0.500	1.98	0.584	0.021	.	.	1.010	.	0.100	last	
VS S20/5	0.270	0.432	0.0080	0.0049	0.304	0.136	1.61	1.73	.	.	.	0.173	0.070	1.48	(0.004)	100 g	
NCS HC28211	0.265	0.934	0.013	0.014	0.312	0.148	0.082	1.13	0.0199	0.018	0.012	0.011	0.070	0.0038	100 g	
VS UNL13/2	0.228	1.60	0.022	0.024	0.553	0.185	0.125	1.11	(0.005)	.	Zr:0.076	.	.	.	100 g	
GBW 01356a	0.212	0.460	0.0174	0.0117	0.270	0.031	.	0.972	.	.	.	0.191	100 g	
VS S10-1/1	0.209	1.04	0.0100	0.0143	0.569	0.111	0.063	0.060	(0.005)	100 g	
NCS HC28209	0.202	1.02	0.017	0.011	0.225	0.141	0.047	1.21	0.0220	0.020	0.013	.	.	0.0035	100 g	
SRM 33e	0.186	0.525	(0.005)	0.009	0.262	0.070	3.36	0.068	0.030	.	.	0.224	150 g	
NM 221	0.18	0.39	0.013	0.014	0.18	.	3.21	0.68	.	.	.	0.23	100 g	
SRM 291	0.177	0.55	0.008	0.020	0.23	0.047	0.065	1.33	(0.002)	.	.	0.53	150 g	
GBW 01351	0.177	0.50	0.017	0.019	0.254	0.170	0.254	0.781	0.067	.	.	0.136	.	.	0.193	150 g	
BCS 406/2	0.173	0.447	0.0102	0.043	0.342	0.289	1.62	2.001	0.013	.	.	0.98	.	0.010	last	
NM 212	0.154	0.51	0.046	0.035	0.287	.	3.05	0.84	100 g	
ECRM 106-2	0.153	0.727	.	.	0.238	0.078	1.430	1.030	.	.	.	0.054	.	.	.	(0.057)	.	.	.	(0.0022)	(0.010)	100 g	
NCS HC23205	0.124	0.527	0.021	0.021	0.																		

CRM MILD STEEL CHIPS, chart 2 of 2 chips 100 g

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Mo	Ti	V	W	B	Ca	Co	Nb	Sn	Zr
JSS 150-19	0.497	0.101	0.0389	0.0292	0.207	0.049	4.00	0.310	0.0157	0.0153	0.195	.	0.0190
IARM 170B	0.400	0.821	(0.005)	(0.004)	0.21	(0.005)	0.197	0.009	0.230	.	(0.003)	(0.19)	(0.002)	.	(0.0004)	.	(0.005)	(0.004)	(0.002)	.
IMZ 1.10/2	0.39	0.48	0.020	0.013	0.24	0.076	0.17	1.46	0.82	.	0.20
IMZ 1.9/3	0.38	0.55	0.025	0.016	0.28	0.101	1.62	1.30	.	.	0.16
IMZ 1.11/3	0.35	0.48	0.025	0.020	0.18	0.077	0.12	1.00	.	.	0.19
IARM 378A	0.274	1.38	0.018	0.037	0.307	0.299	0.142	0.187	(0.0029)	.	0.031	(0.003)	0.0844	(0.006)	(0.0006)	.	0.013	(0.003)	0.0236	.
IARM 169B	0.232	0.75	(0.004)	(0.004)	(0.32)	(0.005)	(0.010)	0.010	0.36	.	(0.004)	0.23	(0.002)	(0.003)	0.0003	.	(0.003)	(0.004)	(0.002)	.
IMZ 1.85	0.205	1.69	0.026	0.026	0.51	0.29	0.24	0.27	(0.064)	0.064	0.007	.	0.093	(0.011)	.	0.026
IMZ 1.19/2	0.20	1.00	0.020	0.017	0.30	0.11	0.096	1.10	.	.	0.084
IMZ 1.73/1	0.18	1.24	0.014	0.029	0.34	0.56	0.095	0.15	0.043	0.036	0.056	.	0.073	0.088	.	.
IMZ 1.31	0.14	0.81	0.022	(0.025)	0.31	0.33	(0.87)	0.55	.	.	0.50	.	(0.10)	.	0.0013
IMZ 1.33	0.14	0.69	(0.022)	(0.014)	0.26	0.43	0.88	0.52	.	.	0.51	.	(0.087)	.	0.0057
IMZ 1.76/1	0.13	1.39	0.022	0.032	0.28	0.058	0.33	0.11	0.042	0.036	0.101	0.068	.	.
IMZ 1.32	0.12	0.80	0.018	0.016	(0.21)	0.37	0.83	0.55	.	.	0.53	.	(0.093)	.	0.0021
IMZ 1.72/1	0.12	0.56	0.019	0.030	0.55	0.88	0.041	0.45	0.032	0.026	.	.	(0.047)
IMZ 1.74/1	0.11	1.95	0.030	0.024	0.20	0.31	0.055	0.25	0.014	(0.009)	.	.	0.094
IMZ 1.34	0.11	0.84	0.014	(0.030)	0.31	(0.05)	0.65	0.73	.	.	0.39	.	(0.005)	.	0.0084
IMZ 1.77/1	0.11	0.37	0.029	0.027	0.18	0.17	0.051	0.32	0.012	(0.008)	.	0.021	0.046
IMZ 1.82	0.10	1.11	0.017	0.020	0.27	0.069	0.085	0.21	0.060	.	0.060	.	0.101	.	.	0.020	.	0.058	.	(0.0015)
IMZ 1.81	0.10	0.28	0.043	0.012	0.28	0.32	0.069	0.58	0.017	0.005
IARM FeT23-18	0.068	0.82	0.012	0.006	0.18	0.046	0.53	2.47	.	0.0044	0.261	(0.004)	0.238	1.60	0.0020	.	0.085	0.052	(0.004)	.
JSS 155-17	0.050	0.205	0.0017	0.0021	0.498	0.407	0.151	3.03	0.0102	0.0095	0.709	.	0.397

RM LOW ALLOY STEEL CHIPS, chart 1 of 2

analysis listed in mass % except * which is mg/g C12X, DH: typical analysis 50 g chips BS CE: 150 g chips all others: 100 g chips

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Al.sol	Al.insol	Co	Mo	N	Nb	Ti	V
BS CE26 *	0.88	0.18	0.042	0.005	0.24
C12X LA50	0.81	0.98	0.057	0.015	0.67	0.09	0.13	0.12	0.19	.	.	.	0.19	.	.	.	0.58
C12X LA40	0.67	0.24	0.044	0.021	0.28	0.29	0.46	0.64	0.19	.	.	.	0.46	.	.	.	0.36
BS CE24 *	0.63	0.84	0.016	0.010	0.27	0.066	0.045	0.016	0.044	.	.	0.010	0.006
IARM 34A	0.51	0.78	0.01	0.010	0.22	0.18	0.14	0.99	0.014	.	.	0.009	0.044	0.0076	0.003	0.003	0.17
DH E2208	0.4843	0.8406	0.0144	0.0013	0.2616	0.0202	0.0416	0.9596	0.0271	.	.	0.0037	0.0105	.	0.0005	0.0018	0.1325
BS CSN-2C	0.469	0.60	0.012	0.0305	0.17	0.073	0.071	0.072	.	.	.	(0.006)	0.0173
DH E2123	0.335	1.237	0.0166	0.0104	0.232	0.0172	0.0209	0.0316	.	0.0289	0.0011	0.0035	0.00271	.	.	0.0465	0.0031
DSZU CX03a	0.206	0.369	0.029	0.033	0.014	0.020	0.0155	0.046	200 g
DH E2110	0.2035	1.483	0.0186	0.0169	0.500	0.056	0.0179	0.023	.	0.0385	0.002	0.0042	0.00249	.	.	0.0014	0.0019
C12X 3550	0.20	0.62	0.028	0.024	0.48	.	.	.	<0.01	.	.	0.05	.	.	0.02	.	0.11

Number	As	B	B.sol	Ca*	O*	Pb	Sb	Sn	W	Zn	Zr
BS CE 26 *
C12X LA50
C12X LA40
BS CE 24 *	0.0029
IARM 34A	(0.006)	(0.0002)	.	.	(14)	.	.	0.009	(0.02)	.	.
DH E2208	0.004	.	.	26	.	.	0.0005	0.0004	.	.	.
BS CSN-2C	.	.	.	33
DH E2123	0.003	0.0022	0.0019	<1	.	0.00008	0.00041	0.00062	.	0.00044	.
DSZU CX03a
DH E2110	0.006	0.00006	.	3	.	0.00048	0.0008	0.00178	.	0.00053	.
C12X 3550	.	0.001	0.08	.	.	.	<0.01

* Clearance Sale Item, no uncertainties
* Clearance Sale Items

RM LOW ALLOY STEEL CHIPS, chart 2 of 2

analysis listed in mass % except * which is mg/kg

C12X, DH: typical analysis 50 g chips

all others: 100 g chips

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Al.sol	Al.insol	Co	Mo	N	Nb	Ti	V
DH E2131	0.1964	.	0.0068	0.0232	0.181	0.0387
C12X 3530 *	0.19	0.82	0.021	0.025	0.14	0.30	0.19	0.49	0.007	.	.	0.058	0.11	0.015	0.10	0.055	0.048
C12X 3500	0.18	0.70	0.029	0.032	0.45	0.15	0.18	0.31	0.35	.	.	0.005	0.10	.	.	0.054	0.002
DH E2119	0.1781	1.605	0.0133	0.0098	0.423	0.0184	0.433	0.0127	.	0.0486	0.002	0.0049	0.00356	.	.	0.0009	0.144
DH E2329	0.168	0.3219	0.0065	0.00067	0.257	0.0216	2.3865	1.7057	0.0436	.	.	0.005	0.4126	0.0045	0.00097	0.0027	0.0025
DH E2303	0.1671	1.744	0.0151	0.0112	0.577	0.05
DH E2132	0.166	1.609	0.0127	0.0094	0.411	0.0178	0.430	0.0124	.	0.0485	.	0.0046	0.0035	.	.	.	0.1465
DH E2203	0.1658	1.6015	0.0126	0.0089	0.419	0.018	0.4342	0.0128	0.0653	.	.	0.0046	0.0036	.	0.0001	0.0008	0.1414
DH E2139	0.1505	1.576	0.0117	0.0052	0.4543	0.0299	0.0232	0.0155	.	0.0319	.	0.0032	0.0027	.	0.0326	0.0010	0.1111
DH E2102	0.147	0.8221	0.0164	0.0012	0.2944	0.3503	0.2825	0.2847	0.0318	.	0.0009	0.0034	0.0192	0.0127	0.0329	0.0010	0.0014
IARM 36B	0.14	0.49	0.010	0.038	0.21	0.13	0.18	2.18	0.030	.	.	0.012	0.95	0.0102	0.004	0.003	0.006
DH E2138	0.1296	1.040	0.0097	0.0009	0.3966	0.6446	1.176	0.1617	0.0322	.	.	0.0049	0.3431	.	0.0191	0.0023	0.0021
DH E2315	0.1103	0.435	0.0887	0.0117	0.514	0.479	0.498	1.049	.	0.0299	0.0005	0.0049	0.0082	.	.	.	0.004
DH E2312	0.090	1.593	0.0159	0.0023	0.458	0.011	1.170	1.938	.	0.0255	.	0.0057	0.203	.	.	.	0.121
DH E2114	0.0827	0.704	0.0121	0.0103	0.050	0.0485	0.051	0.0209	.	0.0465	0.0008	0.0035	0.00668	.	.	0.213	0.0081
DH E2327	0.0801	1.7182	0.018	0.0015	0.3886	1.3256	0.8964	0.0328	0.0217	.	.	0.0052	0.2785	0.0143	0.0906	0.0010	0.0037
DH E2144	0.080	0.708	0.012	0.0103	0.05	0.0488	0.0506	0.0209	.	0.0459	.	0.0035	0.0061	.	.	0.213	0.008
DH 853-2	0.080	0.708	0.0120	0.0103	0.050	0.0488	0.0506	0.0209	.	0.0460	.	0.0035	0.0061	.	.	0.213	0.008
DH E2193	0.074	1.471	0.00273	0.0008	0.314	0.0463	0.0743	0.0144	.	0.0396	.	0.0033	0.0668	.	0.0002	0.0011	0.0329
DH E2210	0.0648	1.4783	0.013	0.0034	0.0872	0.1035	0.2443	0.0344	0.0439	.	.	0.0031	0.0162	0.0212	0.0164	0.0164	0.0014
DH E2314	0.061	0.392	0.0058	0.0011	0.164	0.005	5.39	0.010	.	.	0.0014	0.0047	0.054	.	.	.	<0.001
C12X LA10	0.06	1.32	0.013	0.045	0.75	0.034	0.21	0.85	<0.01	.	.	.	<0.01	.	.	.	0.41
DH E2319	0.0539	0.5907	0.0079	0.0006	0.2347	0.017	9.314	0.020	0.043	.	.	0.0066	0.073	.	0.0003	0.0018	0.0017
DH E2130	0.0457	0.324	0.0101	0.0279	0.0304	0.0191	0.0215	0.0152	.	0.0624	.	0.0021	0.003	.	.	.	<0.001
DH E2309	0.0438	2.031	0.0168	0.00078	0.2006	0.0083	0.026	0.029	.	.	.	0.0044	0.3203	.	0.0558	0.0163	0.0075
DH E2194	0.0396	1.3431	0.0091	<0.0006	0.2733	0.0174	0.035	0.0333	0.0436	.	.	0.0035	0.0055	.	0.0329	0.0017	0.0351
DH E2140	0.0362	0.2912	0.0069	0.0127	0.0091	0.0098	0.024	0.0075	.	0.0300	0.0021	0.0048	0.0018	.	.	.	<0.002
DH 136-2	0.0362	0.2912	0.0069	0.0127	0.0091	0.0098	0.0240	0.0075	.	0.0300	.	0.0048	0.0018	.	.	.	0.001
C12X LA60	0.01	0.10	0.005	0.006	0.06	0.01	0.03	0.03	<0.01	.	.	.	<0.01	.	.	.	<0.01
DH E2141	.	1.468	.	.	0.4575	0.0312	.	.

Number	Ag	As	B	Bi	Ca	Ce	In	O*	Pb	Sb	Sn	W	Zn	Zr
DH E2131
C12X 3530 *	.	0.057	.	0.020	.	.	Se:0.018	.	0.016	0.16	0.078	0.10	0.050	.
C12X 3500	.	0.070	0.03	0.29	.	.
DH E2119	<0.00001	0.0034	0.00008	.	<0.0002	.	.	.	0.00013	0.0004	0.00058	.	0.00036	.
DH E2329	.	0.002	<0.00009	.	0.0027	.	.	.	<0.00007	0.00053	0.00052	.	.	.
DH E2303	.	0.003
DH E2132	.	0.0035	.	.	0.0001
DH E2203	.	0.0027	.	.	<0.0001	.	.	.	0.0004	0.0004	0.0008	.	.	.
DH E2139	.	0.0047	.	.	0.0014	.	.	.	0.0503	0.0006	0.0014	.	0.0006	.
DH E2102	.	0.0043	<0.0001	.	0.0012	.	.	.	<0.0001	0.0005	0.0006	.	0.0003	.
IARM 36B	.	0.009	(0.002)	.	0.0002	.	18	(0.003)	.	0.008	(<0.01)	.	.	.
DH E2138	.	0.002	.	.	0.0017	.	.	.	0.0001	0.0006	0.0007	.	0.0001	.
DH E2315	.	0.0029	.	.	0.0001	.	.	.	0.0002	0.0004	0.0005	.	0.0007	.
DH E2312	.	.	0.00005	.	0.0013	.	.	.	0.0002	0.0005	0.0003	.	0.0007	.
DH E2114	0.00001	0.0056	<0.00004	.	<0.0001	.	<0.0001	.	0.00018	0.00078	0.00522	.	0.00067	.
DH E2327	.	0.0025	<0.00014	.	0.0051	.	.	.	0.0007	0.00049	0.0028	.	.	.
DH E2144	.	0.006	0.0002	0.0007	0.0052	.	0.0005	.
DH 853-2	.	0.0060	0.0002	0.0007	0.0052	.	0.0005	.
DH E2193	.	0.0022	.	.	0.0023	.	.	.	<0.0001	0.0006	0.0056	.	.	.
DH E2210	.	0.0019	.	.	0.0003	0.0005	0.0005	.	.	0.0071
DH E2314	0.0034	.	.	.	0.0001	0.0008	0.0002	.	0.0005	.
C12X LA10
DH E2319	.	0.0036	.	.	0.0016	.	.	.	0.0003	0.0005	0.0005	.	0.0004	.
DH E2130	.	0.0062	.	.	0.0001	<0.001	.	.	.
DH E2309	.	0.0019	0.0026	.	0.0016	.	.	.	0.00004	0.0005	0.0009	.	<0.0002	.
DH E2194	.	0.0023	.	.	0.001	.	.	.	0.0001	0.0004	0.0005	.	0.0004	.
DH E2140	.	0.0035	.	.	0.0001	.	.	.	0.0001	0.0007	0.0005	.	0.0012	.
DH 136-2	.	0.0035	.	.	0.0001	.	.	.	0.0001	0.0007	0.0005	.	0.0012	.
C12X LA60
DH E2141	0.0265

* Provisional Analysis

last of stock, sale price

last of stock, sale price

RESULFURIZED STEEL

= class, where 1 = CRM and 2 = RM

C12X, C14X typical analysis

100 g units

#	Number	S	C	Mn	P	Si	Cu	Ni	Cr	Al	Co	Mo	N	Ti	V	W	As	Pb	Sb	Sn	Zn
1	IMZ C-123	0.38	0.25	1.57	0.030	0.23	0.093	0.057	0.16	0.032	.	.	0.0171	.	.	.	0.033	0.030	0.030	(0.007)	.
1	ECRM 085-1C	0.336	0.067	0.977	0.062	0.008	0.291	.	.	.	0.019	.	.	.	0.0021	.	.	0.0010	0.0073	.	0.0025
1	IPT 41B	0.322	0.072	1.08	0.057	0.022	0.005	0.012	0.037	0.220	.	.	.
1	IRSID 022-1	0.300	0.115	0.797	0.057
1	IARM 199C	0.281	0.469	1.55	0.0155	0.21	0.193	0.085	0.190	0.0019	0.007	0.0293	0.0070	0.0016	(0.0037)	0.0023	0.0059	(0.001)	(0.003)	0.0084	(0.0006)
1	IMZ C-124	0.28	0.10	0.60	0.082	(0.019)	0.060	0.046	0.11	0.005	.	.	0.0059	.	.	.	0.004	(0.002)	0.002	0.009	.
1	IRSID 024-1	0.235	0.104	0.726	0.018	0.139	0.287	.	.	.
1	IMZ C-122	0.21	0.27	1.33	0.073	0.43	0.25	0.25	0.19	(0.027)	.	.	0.0110	.	.	.	0.007	(0.020)	0.019	0.12	.
1	VS U2/7	0.193	0.136	1.19	0.040	0.046	0.082	0.076	0.158	(0.005)	0.166	.	.	.
1	ECRM 058-2C	0.1712	0.424	1.186	0.0098	0.1080	0.261	0.199	0.1211	.	.	0.0589	0.0107	.	.	.	0.0095
1	ECRM 051-1	0.126	0.181	1.18	(0.025)	(0.11)	(0.15)	(0.14)	(0.05)
1	C12X 3520	0.125	0.30	0.63	0.067	0.33	0.14	0.33	0.415	0.145	0.050	0.255	.	0.28	0.058	0.22	0.010	.	0.022	0.106	.
1	IARM 29E	0.121	0.193	1.19	0.0157	0.239	0.253	0.082	0.105	0.0032	0.008	0.0269	0.0093	0.0014	0.0255	.	0.0085	(0.001)	(0.003)	0.0109	(0.004)
1	IARM 348A	0.102	0.384	1.46	0.0121	0.270	0.230	0.081	0.123	(0.002)	(0.010)	0.026	(0.010)	0.0015	0.0029	(0.009)	(0.007)	(0.002)	(0.003)	0.0112	<0.003
1	IMZ C-121	0.097	0.39	1.18	0.057	(0.056)	0.032	0.029	0.036	0.016	.	.	0.0125	.	.	.	0.002	0.011	0.017	0.059	.
1	IARM 307A	0.096	0.163	1.44	0.0113	0.281	0.190	0.197	0.104	0.032	(0.010)	0.045	0.0108	0.0015	(0.0028)	(0.005)	0.008	(0.002)	<0.004	0.0090	<0.002
1	IARM 307B	(0.094)	0.162	1.45	(0.012)	(0.30)	0.191	0.195	0.105	0.034	0.0101	0.045	(0.011)	(0.003)	(0.003)	0.010	.
1	IMZ C-125	(0.057)	0.029	0.95	(0.018)	0.15	0.044	0.023	0.18	(0.007)	0.065	.	0.014	0.002	.

SILICON STEEL CHIPS WITH NITROGEN

= class, where 1 = CRM and 2 = RM

100 g units

#	Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	As	Co	Mo	N	Nb	Sn	Ti	V	W
1	ECRM 191-2C	3.267	0.0043	0.1334	0.0087	0.0029	0.0165	0.0224	0.0314	0.985	.	0.0018	.	0.0020	0.00105	.	0.0050	0.0024	.	.
1	NCS HC14213	3.18	0.076	0.081	0.0090	0.023	0.066	.	.	.	0.031	.	.	.	0.0081	.	.	.	0.138	.
1	VS S9/4 **	3.12	0.040	0.066	0.0063	0.0034	0.139	0.097	0.044	0.0106	0.0074	0.0061	0.0101	0.0050	0.0130	.	0.0040	0.0057	0.0009	.
2	TH 1016	(2.95)	.	(0.09)	(0.01)	.	(0.02)	(0.01)	(0.02)	.	0.0263	.	.	.	0.0067
1	IMZ 1.22/1	2.02	0.090	0.24	0.019	0.026	0.071	0.039	0.045	0.014	0.011	0.020	.	.	0.0039	.	0.0076	(0.004)	.	.
1	ECRM 196-2C	1.808	0.0060	0.364	0.00369	0.00065	0.0057	0.0401	0.0282	0.2167	.	0.00033	0.0138	0.0142	0.00178	.	0.00047	0.00253	0.00368	.
1	IARM 340A	1.63	0.414	0.755	0.011	0.001	0.103	1.80	0.84	0.062	.	(0.004)	0.006	0.39	0.0020	0.015	0.005	0.0098	0.064	(0.005)
1	IMZ 1.8/4	1.31	0.35	0.99	0.020	0.018	0.11	0.16	1.18
2	IARM 172A	1.29	0.78	0.010	0.007	0.004	0.40	0.025	3.52	0.39	.	(0.005)	0.006	0.014	0.0004	0.004	0.003	0.003	0.003	0.038
1	IMZ 1.21/1	1.29	0.058	0.16	0.013	0.024	0.068	0.056	0.037	0.005	0.003	0.019	.	.	0.0030	.	0.0067	(0.005)	.	.
1	BCS 404/2	1.121	0.696	0.532	0.0479	0.0228	0.427	0.393	0.774	0.017	.	.	.	0.307	0.0089	.	.	.	0.107	.
1	ECRM 181-1	1.054	0.590	1.047	0.018	0.035	0.174	0.070	0.126	0.022	0.0068
1	BCS 113	0.931	0.837	1.207	0.0595	0.0294	0.179	0.0784	1.248	0.0151	.	0.0020	0.0415	0.056	0.0109	0.0487	0.0067	0.0390	0.201	0.012

Number	B	Ca	Mg	O	Pb	Sb	Zn	Zr
ECRM 191-2C
NCS HC14213
VS S9/4	.	.	0.0007	.	0.0029	0.0009	0.0006	.
TH 1016
IMZ 1.22/1	0.0028	.	.	.
ECRM 196-2C	0.00014	0.00071	0.00075	.	.	0.00019	.	.
IARM 340A	0.0004	.	(0.0010)	.	0.0021	.	.	.
IMZ 1.8/4
IARM 172A	0.0003	.	0.0006
IMZ 1.21/1	0.0025	.	.	.
BCS 404/2
ECRM 181-1
BCS 113	0.0066	0.0029	.

SILICON STEEL CHIPS

C12X: typical analysis 50 g BS CE: 150 g all others: 100 g

Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	W	As	Bt	Bs	Sn
CRM																			
VS S57/1	3.54	0.256	.	0.0051	0.0039	.	0.758	2.98	.	.
ECRM 151-1 *	3.49	0.028	0.085	0.015	(0.025)
CMSI 1232	3.36	0.057	0.225	0.0124	0.020	0.314	0.316	0.259	0.166	.	.	0.0036
NCS HC20210	3.36	0.057	0.225	0.012	0.020	0.314	0.316	0.259	0.1679	0.166	.	0.0036
CMSI 1432	2.91	0.400	0.437	0.0064	0.0029	0.64	0.064	0.159	.	0.113	.	0.012	.	.	1.18
SRM 125b	2.889	0.0261	0.2751	0.0276	0.0095	0.0707	0.0375	0.0198	0.329	.	(0.007)	0.0087	(0.004)	(0.0005)	.	(0.003)	.	.	0.0034
CMSI 1431	2.15	0.051	0.600	0.0149	0.0174	0.195	0.276	0.362	.	0.065	.	0.160	.	0.043	0.77
IPT 108	1.96	0.598	0.861	0.028	0.020	0.121	0.052	0.133	.	0.019	0.006	0.017	0.004
CMSI 1435	1.74	0.666	0.725	0.0144	0.0190	0.147	0.081	0.071	.	0.132	.	0.061	.	0.129	0.40	.	.	0.0013	.
ECRM 186-1C	1.72	0.610	0.870	0.022	0.035	0.281	0.190	0.218	0.014	.	.	0.048
BCS 405/1	1.71	0.032	1.28	0.018	0.069	0.013	0.22	0.15	.	.	.	0.002	.	0.28
CMSI 1433	1.69	0.599	1.14	0.0209	0.0291	0.095	0.124	1.13	.	0.018	.	0.071	.	0.081	0.028
VS S15/5	1.69	0.558	0.701	0.0140	0.0185	0.205	0.135	0.199	(0.005)	.	.	.
IARM 342A	1.63	0.257	1.37	0.006	0.0051	0.110	1.76	0.38	0.019	N:0.0102	0.008	0.42	0.0028	0.023	(0.005)	(0.006)	O:0.0006	B:0.0004	0.021
BCS 409/1	1.46	0.082	0.44	0.025	0.021	0.048	3.06	0.94	.	.	0.014	0.65	.	0.09
CMSI 1108	1.42	1.086	0.308	0.013	0.004	0.036	0.021	0.045	.	0.11	.	0.89	0.30	0.50	.	.	.	0.016	.
BCS 405	1.38	0.058	1.28	0.017	0.060	0.015	0.12	0.21	.	.	.	0.017	.	0.32	last
IMZ 1.8/4	1.31	0.35	0.99	0.020	0.018	0.11	0.16	1.18
VS S22/4	1.29	0.348	0.606	0.0090	0.0060	0.167	0.850	2.83	.	.	.	0.426	.	0.189	0.8	(0.005)	.	.	.
VS S58	1.27	0.348	1.25	0.0076	0.0077	0.100	0.086	0.123

Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	W	As	Bt	Bs	Sn
DSZU C58	1.27	0.348	1.25	0.0076	0.0077	0.100	0.086	0.123	250 g
BCS 409/2	1.18	0.086	0.559	0.0141	0.0179	0.205	3.02	1.318	0.094	.	.	0.599	.	0.008
CMSI 1434	1.10	0.706	0.875	0.0256	0.0374	0.303	0.393	0.760	.	0.158	.	0.273	.	0.168	0.176	.	.	0.0012	.
CMSI 1189	1.09	0.283	0.438	0.022	0.023	0.247	0.224	0.300	0.132	0.128	.	.	0.171	0.144	.	.	0.0045	0.0041	.
BCS 409 *	1.07	0.11	0.48	0.025	0.015	0.23	3.14	1.22	.	.	.	0.77	.	0.028
CMSI 1102	1.07	0.056	1.20	0.127	0.093	0.073	0.66	2.88	.	0.40
NCS HC28304	1.06	0.407	0.315	0.015	0.013	0.017	0.037	5.08	0.0096	0.0056	.	1.20
BCS 404	1.04	0.67	0.52	0.050	0.018	0.31	0.46	0.68	.	.	.	0.33	.	0.100	.	.	.	last of stock	.
NCS HC20212	0.998	0.162	0.346	0.036	0.030	0.213	0.103	0.471	0.2090	0.208	.	0.0048
BAM 128-1	0.949	0.085	0.839	0.007	0.007	0.055	0.046	0.108	0.286	.	.	.	0.890	(0.008)
BCS 405/2	0.947	0.044	0.903	0.0095	0.058	0.022	0.102	0.206	0.330	.	.	0.025	.	0.411
RM																			
C12X LA90	1.07	0.47	0.58	0.074	0.065	0.51	2.04	3.10	0.05	.	0.30	1.10	.	0.39	0.007
C12X LA20	0.98	0.24	0.55	0.026	0.042	0.44	0.73	0.81	0.03	.	.	0.10	.	0.09

Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	W	As	Bt	Bs	Sn
--------	----	---	----	---	---	----	----	----	----	-----	----	----	----	---	---	----	----	----	----

CRM	TOOL STEEL CHIPS WITH NITROGEN												JK 49C: 35 g	other JK, JSS, NCS, SRM: 150 g	all others: 100 g						
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn
ECRM 288-1C	2.08	0.292	0.024	(0.0012)	0.260	0.060	0.298	12.00	0.012	0.018	0.103	0.0151	.	.	0.055	(0.68)	(0.0065)
ECRM 274-1C	1.563	0.397	0.0148	0.0096	1.057	0.0281	0.077	8.036	(0.0025)	(0.0230)	1.4551	0.0769	.	(0.0011)	4.010	0.0087	(0.0013)	(0.0005)	(0.0026)	(0.000064)	(0.001)
IARM 41D	1.519	0.256	0.021	0.012	0.256	0.047	0.114	11.5	0.014	(0.020)	0.74	0.0152	(0.004)	(0.003)	0.77	0.034	(0.01)	(0.0006)	(0.003)	(0.0008)	(0.005)
IARM 45B	1.42	0.90	0.010	0.008	0.92	0.018	0.024	0.061	0.010	0.004	0.24	0.0080	(0.002)	0.002	(0.003)	(0.004)	(0.002)	(0.0001)	(0.0005)	.	0.008
IARM 251A	1.398	0.33	0.014	0.058	0.58	0.13	0.131	4.1	0.01	0.129	5.16	0.044	0.016	0.003	3.9	5.5	0.016	(0.002)	(0.01)	(0.002)	0.011
IARM FeM62-18	1.32	0.27	0.016	0.015	0.37	0.115	0.129	3.86	(0.006)	0.105	10.2	0.045	(0.017)	(0.003)	2.02	6.31	.	(0.003)	(0.003)	.	.
JSS 610-11	1.252	0.301	0.0171	0.00014	0.310	0.0239	0.046	4.04	.	9.72	3.05	0.0349	.	.	3.32	9.22
ECRM 283-1	1.219	0.217	0.022	0.029	0.345	.	.	4.15	.	10.27	3.41	0.033	.	.	3.28	9.66	.	0.0003	.	.	.
ECRM 268-1C	1.134	0.293	0.0209	0.0154	0.373	0.123	0.143	4.57	.	0.0290	3.20	2.03	.	.	8.47	3.70	0.0062	0.0009	.	Sb:0.0017	0.0078
IMZ C-172	1.03	0.71	0.018	0.047	0.21	0.128	0.132	4.47	0.062	0.012	0.96	0.0192	.	(0.002)	0.20	0.011	0.010
IARM 39B	0.99	0.54	.	0.35	0.004	0.10	.	4.79	0.006	0.014	1.01	0.0096	0.006	0.22	(0.026)	0.14	.	.	0.017	0.003	0.003
IARM 39C	0.99	0.45	0.019	0.007	0.28	0.077	0.144	4.99	0.017	0.013	0.97	0.011	0.0040	0.0029	0.21	0.011	(0.005)	0.001	0.001	(0.0001)	0.005
BAM 227-1	0.950	0.236	0.016	0.022	0.272	0.124	0.114	4.25	.	.	2.64	0.040	.	.	2.44	3.03
IARM 320A	0.93	0.33	0.021	(0.0015)	0.36	0.091	0.204	4.22	0.023	4.90	4.79	(0.014)	(0.015)	0.0032	1.76	6.01	0.013	0.0011	(0.0021)	.	0.008
ECRM 290-1C	0.91	0.24	0.016	0.016	0.08	0.081	0.33	4.18	.	5.12	4.81	0.0325	.	.	1.92	6.24
JSS 609-11	0.897	0.287	0.0246	0.00059	0.252	0.0494	0.1234	3.96	.	4.72	4.83	(0.0215)	.	.	1.87	6.15
JK 12A	0.886	0.312	0.020	0.023	0.30	0.062	0.191	4.04	.	0.189	4.85	0.0259	.	.	1.94	6.42	.	.	.	0.0004	0.007
IARM 304A	0.857	0.260	0.019	0.0016	0.36	0.14	0.133	3.55	0.009	0.278	8.04	0.034	0.021	0.002	1.23	1.65	(0.01)	0.002	0.002	.	0.006
IARM 306B	0.84	0.24	0.006	(0.001)	0.21	0.058	0.095	4.12	0.08	0.010	4.2	0.0049	0.007	(0.002)	0.98	(0.01)	(0.003)	(0.001)	Sb:0.0025	(0.001)	0.004
IARM 44C	0.82	0.301	0.027	0.004	0.31	0.12	0.132	4.04	0.05	0.247	5.02	0.033	0.012	0.004	1.91	6.0	(0.01)	(0.002)	(0.003)	(0.002)	0.010
IARM FeT1-18	0.80	0.295	0.026	(<0.0010)	0.30	0.034	0.14	3.98	0.054	0.096	0.124	0.0195	(0.004)	0.026	1.05	18.0	.	.	(0.0027)	.	(0.010)
IARM 281A	0.74	0.30	0.015	0.019	0.29	0.096	0.15	3.89	0.007	4.8	0.49	0.0064	0.094	0.004	0.90	17.6	(0.02)	(0.003)	(0.003)	.	0.02
IARM 40C	0.72	1.91	0.014	0.012	0.32	0.142	0.255	0.99	0.019	0.010	1.27	0.0083	0.003	0.008	0.010	0.009	0.008	0.0009	0.0013	.	0.008
SRM 50c	0.7193	0.3417	0.0222	0.006367	0.3102	0.0792	0.0686	4.128	.	(0.035)	0.0821	0.0117	.	.	1.158	18.445	0.0225	.	.	.	0.0183
IARM 43B	0.711	0.56	<0.005	0.251	0.013	0.180	0.0016	6.651	0.021	0.012	0.206	0.0093	0.004	0.0035	<0.005	1.39	0.005	0.0002	0.008	0.013	0.0047
IARM 40B	0.68	1.98	.	0.39	0.004	0.050	(0.0014)	1.04	(0.006)	0.015	1.22	0.0107	0.005	0.014	0.013	0.096	.	(0.0010)	0.012	0.003	0.003
IARM 47B	0.59	0.79	0.017	0.006	1.96	0.17	0.090	0.23	0.014	0.007	0.20	0.0092	(0.002)	0.010	0.17	(0.016)	.	(<0.001)	(0.0014)	(0.0003)	0.008
JSS 605-11	0.554	0.758	0.0197	0.0109	0.256	0.155	1.661	1.008	.	.	0.457	0.0192	.	.	0.1014	0.0104
IARM 259A	0.479	0.399	0.020	0.0007	0.44	0.081	0.194	3.27	0.016	0.011	1.43	0.0077	0.003	0.0026	0.256	0.035	0.006	0.0003	0.0014	<0.0005	0.004
IARM 46B	0.45	0.27	0.019	0.0040	0.89	0.147	0.108	1.09	0.011	0.013	0.222	0.0069	0.003	0.007	0.170	1.96	(0.01)	0.0003	0.002	<0.002	0.016
IARM 255A	0.403	0.27	0.013	0.0012	0.93	0.049	0.083	4.84	0.01	0.009	1.33	0.0067	0.004	0.002	0.43	0.007	(0.002)	0.0004	0.0011	<0.001	0.006
ECRM 276-2C	0.399	0.365	0.0093	0.0189	1.034	0.183	0.203	4.975	.	.	1.134	0.0116	.	.	0.296	0.0133
IARM 42C	0.382	0.40	0.022	0.0037	0.85	0.066	0.051	4.86	0.018	0.022	1.29	0.0201	(0.004)	0.0125	0.84	0.32	(0.01)	0.0011	0.003	0.0007	(0.006)
ECRM 271-1C	0.3698	0.437	0.0120	0.00045	0.923	0.1371	0.1552	5.002	0.0234	0.0139	1.247	0.0137	.	0.0020	0.850	0.0054	0.0057	Ca: 0.0009	.	.	0.0084
IMZ C-174	0.33	0.32	0.029	0.023	0.93	0.17	0.13	5.10	0.080	0.011	1.24	0.0288	.	(0.001)	0.98	0.021	0.010
IMZ C-173	0.30	0.43	0.029	0.020	1.15	0.32	0.42	5.52	0.060	(0.013)	1.50	0.0342	.	(0.002)	0.47	0.10	0.012
JSS 603-8	0.30	0.31	0.012	0.012	0.32	0.055	0.084	2.32	.	.	0.13	0.0250	.	.	0.46	5.47
IARM 341A	0.298	0.226	0.0038	0.0008	0.10	0.143	7.16	0.99	0.032	4.4	1.01	0.0025	(0.005)	0.003	0.086	(0.01)	Ca:0.0011	0.0005	0.0008	(0.001)	(0.005)
IMZ C-178	0.29	0.65	0.016	0.003	0.28	0.140	2.09	1.26	0.051	0.015	0.20	0.0160	0.105	.	0.011	0.017	0.011
IMZ C-171	0.195	0.42	0.020	0.014	0.21	0.116	0.59	11.44	0.036	0.024	1.23	0.057	.	(0.001)	0.26	0.008
IMZ C-170	0.155	0.50	0.018	0.014	0.32	0.285	0.63	8.82	0.11	(0.022)	0.88	0.065	0.087	(0.002)	0.24	(0.19)	0.007
IMZ C-176A	0.15	0.75	0.018	0.003	0.35	0.103	3.62	0.41	(0.058)	(0.010)	0.027	0.0129	.	.	(0.061)	(0.015)	0.009
IMZ C-179	0.114	0.83	0.016	0.003	0.375	0.164	9.98	0.20	0.061	0.016	0.12	0.0108	(0.004)	.	0.023	(0.023)	(0.007)	.	.	.	0.010
IARM FeF9-18	0.104	0.459	(0.011)	0.0036	0.345	0.093	0.148	8.72	.	0.013	0.94	0.0323	0.078	0.0028	0.214	0.0030	0.006	.	0.0025	.	0.0062
IMZ C-175	0.099	0.25	0.016	0.0040	0.22	0.130	3.12	0.515	0.043	(0.013)	0.025	0.0099	.	.	0.014	(0.019)	0.011
IMZ C-157	0.095	0.63	0.015	0.010	0.59	0.066	0.50	9.51	0.26	.	0.71	0.051	.	0.044	0.26
IMZ C-177	0.076	0.32	0.013	0.003	0.24	0.110	8.33	0.18	0.043	(0.017)	0.022	0.0089	.	.	0.010	0.008
IARM 168A	0.003	0.12	0.030	0.064	0.46	0.009	2.32	0.004	0.19	0.003	0.69	0.0002	0.003	0.004	0.004	0.52	(0.003)	0.0004	0.0008	(<0.01)	0.003

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn
--------	---	----	---	---	----	----	----	----	----	----	----	---	----	----	---	---	----	---	---	----	----

TOOL STEEL CHIPS

= Class, where 1 = CRM and 2 = RM C14X: typical analysis 50g IPT 50: 120g NCS HC174xx, HC23503: 100g other NCS, SRM: 150g others: 100g

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Nb	Ti	V	W	Sn
1	CMSI 1406	2.00	0.294	0.049	0.0053	.	.	0.113	11.71	0.96	150g
1	IMZ 1.25/3	1.48	0.26	0.018	0.025	0.28	.	.	0.48	0.29	4.97	.
1	IPT 67	1.27	0.256	0.036	0.007	0.26	0.092	0.32	4.33	.	.	9.79	4.39	.	.	2.58	8.03	.
1	CMSI 1405	1.14	0.287	0.014	0.0046	.	0.040	0.073	0.183	2.31	150g
1	VS S26/5	1.0	0.4	0.02	0.01	0.4	0.14	0.2	4.0	.	.	5.5	0.3	.	.	2.3	10.0	.
1	NCS HC17405	0.941	0.441	0.023	0.028	0.521	.	0.095	1.99	.	.	.	0.122	.	.	0.18	19.22	.
1	IPT 50	0.916	0.280	0.031	0.015	0.326	0.091	0.33	4.49	.	.	0.260	5.54	.	.	2.00	6.40	.
1	VS S24/5	0.9	0.4	0.02	0.01	0.2	0.2	0.2	3.0	.	.	0.07	3.4	.	.	2.2	5.5	.
1	ECRM 254-1	0.88	0.30	0.023	0.029	0.19	0.09	0.12	5.12	.	.	0.32	4.92	.	.	1.94	6.97	0.019
1	SRM 132b	0.864	0.341	0.012	0.004	0.185	0.088	0.23	4.38	.	.	0.029	4.9	.	.	1.83	6.28	.
1	CMSI 1401	0.855	0.275	0.0261	0.011	0.232	0.041	0.046	4.08	.	.	.	4.84	.	.	2.02	5.99	100g
1	BCS 484	0.85	0.21	0.030	0.024	0.20	.	.	5.17	.	.	10.2	1.07	.	.	0.93	22.4	.
1	NCS HC28402	0.847	0.296	0.023	0.012	0.190	0.122	0.096	3.99	.	0.0020	0.023	5.06	.	0.0013	1.93	6.14	.
2	C14X HS30	0.84	0.59	0.019	0.020	0.58	0.04	0.33	4.65	.	.	10.1	1.06	.	.	1.17	19.1	.
1	ECRM 251-1	0.84	0.27	0.024	0.025	0.21	0.08	0.15	5.35	.	.	5.70	0.53	.	.	1.59	19.9	0.025
1	IMZ 1.14/4	0.83	0.33	0.028	(0.005)	0.35	.	0.16	4.09	.	.	.	0.45	.	.	1.23	17.30	.
1	NCS HC21401	0.828	0.283	0.028	0.0072	0.226	0.140	0.083	4.08	.	0.013	0.018	3.13	.	0.0044	1.33	9.23	0.017
1	SRM 134a	0.808	0.218	0.018	0.007	0.323	0.101	0.088	3.67	.	.	.	8.35	.	.	1.25	2.00	.
2	C14X HS10	0.79	0.29	0.020	0.022	0.195	0.05	0.10	3.93	.	.	0.51	1.11	.	.	0.90	16.8	.
1	NCS HC17406	0.78	0.427	0.024	0.020	0.230	.	0.134	3.64	.	.	.	0.176	.	.	0.44	18.72	.
1	VS S27/4	0.772	0.317	0.0154	0.0138	0.397	0.045	0.288	4.23	.	.	0.017	0.353	.	.	1.19	17.62	.
1	CMSI 1404	0.762	0.280	0.0241	0.026	.	0.038	0.040	4.03	.	.	.	0.245	.	.	1.30	18.16	100g
1	NCS HC20505	0.73	0.26	0.009	0.004	0.25	3.98
1	NCS HC17407	0.710	0.268	0.029	0.0064	0.183	.	0.187	4.29	.	.	.	0.266	.	.	1.05	17.64	.
1	VS S25/4	0.702	0.192	0.0057	0.0053	0.276	0.143	0.242	3.31
1	BCS 482	0.70	0.28	0.021	0.025	0.13	.	.	4.09	.	.	0.24	0.27	.	.	0.98	18.1	.
1	BCS 481	0.69	0.29	0.021	0.027	0.14	.	.	3.56	.	.	0.21	0.22	.	.	0.52	14.2	.
1	BCS 483	0.67	0.29	0.019	0.025	0.11	.	.	3.21	.	.	1.94	0.17	.	.	0.54	10.8	.
1	NCS HC17408	0.577	0.233	0.015	0.0043	0.383	.	0.231	2.70	.	.	.	0.330	.	.	0.81	16.24	.
1	IPT 145	0.558	0.716	0.016	0.011	0.259	0.051	1.61	1.14	0.023	0.021	0.024	0.494	.	.	0.094	.	.
1	IPT 117	0.515	0.557	0.019	0.011	0.349	0.070	3.01	1.03	.	0.026	0.014	0.292	.	.	0.015	0.060	.
1	VS S28/5	0.503	0.339	0.0091	0.0044	0.888	0.024	0.605	6.02	1.59	.	0.0073	0.599	Pb:0.00015	.	0.64	3.46	Sb: 0.0004 Zn: 0.0012
1	CMSI 1182	0.503	0.326	0.0212	0.015	0.592	0.028	0.140	1.14	2.22	150g
1	NCS HC17409	0.493	0.343	0.304	0.0048	0.493	.	0.278	4.78	.	.	.	0.411	.	.	1.49	14.96	.
1	VS S60	0.405	0.634	0.0206	0.0071	0.932	0.120	0.405	13.10	.	.	.	0.135	.	.	0.137	.	.
1	IARM 255B	0.389	0.317	0.010	(0.002)	0.91	0.073	0.062	4.82	0.032	.	0.0090	1.30	(0.006)	.	0.515	.	(0.006)
1	IPT 114	0.388	0.361	0.021	0.0023	1.02	0.064	0.165	5.20	.	0.028	0.018	1.29	.	.	0.89	0.174	.
1	CMSI 1402	0.359	0.298	0.0211	0.021	.	0.030	0.0208	2.48	.	.	.	0.055	.	.	0.27	8.39	100g
1	IRSID 112-1	0.348	0.191	.	.	1.00	0.115	0.234	4.78	.	.	.	1.21	.	.	0.604	1.78	.
1	IMZ 1.13/3	0.33	0.38	0.023	0.007	0.23	0.13	1.52	2.61	0.29	8.31	.
1	NCS HC17414	0.322	2.719	0.0228	0.0177	1.16	.	0.862	4.43	1.955	.	2.939	6.16	0.497	.	1.083	9.22	.
1	IMZ 1.26/2	0.31	0.48	0.021	0.009	0.29	0.14	4.05	1.87	.	.	.	0.11	.	.	.	1.70	.
1	CMSI 1254	0.177	0.509	0.021	0.005	0.27	0.083	4.06	1.51	1.34	.
1	IMZ 1.43	0.14	0.66	(0.010)	0.013	0.60	.	1.06	10.83	.	.	.	0.82	(0.43)	.	0.69	0.92	.
1	SRM 133b	0.128	1.07	0.018	0.328	0.327	0.080	0.230	12.63	<0.005	.	.	0.052	.	.	0.071	.	(0.004)
1	VS S23/5	0.047	0.216	0.0062	0.0066	0.445	0.024	0.054	5.02	0.515	0.74	.
1	BCS 422	(0.036)	(0.09)	(0.015)	(0.025)	(0.06)	1.28	.
1	BCS 423	(0.030)	(0.07)	(0.017)	(0.027)	(0.05)	2.06	.
1	BCS 424	(0.024)	(0.09)	(0.02)	(0.024)	(0.05)	3.02	.
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Nb	Ti	V	W	Sn

last of stock

LOW NICKEL STAINLESS STEEL CHIPS WITH NITROGEN

= Class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg C13X: typical analysis 100g CMSI, JK, JSS, SRM: 150 g chips all others: 100 g chips

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	As	B	Ca*	O	Pb*	Sn	W	
1	IARM 13D	1.040	0.697	0.0195	0.0012	0.614	0.184	0.256	16.36	(0.006)	0.0212	0.488	0.0492	0.0074	0.0035	0.058	(0.008)	0.0005	(7)	0.0031	.	0.011	0.046	
1	IARM 353A	0.98	0.95	0.019	0.025	0.49	0.13	0.265	17.01	0.0018	0.032	0.50	0.027	(0.011)	0.0015	0.116	(0.004)	(0.0006)	(3)	(0.005)	Se:0.17	0.0056	0.041	
1	ECRM 291-1C	0.90	0.81	0.017	0.0088	0.91	0.071	0.56	17.15	.	0.0233	2.10	0.1142	.	.	0.39	
1	IPT 22	0.628	0.804	0.029	0.009	0.449	0.050	0.143	16.21	.	.	.	0.008	
1	BAM 226-1	0.416	0.434	0.0207	0.0094	0.514	.	0.139	13.67	.	.	0.024	0.0362	.	.	0.022	
1	IARM 352A	0.341	1.13	0.0182	0.21	0.357	0.148	0.269	13.11	(0.0025)	(0.016)	0.38	0.029	(0.012)	0.0015	0.028	(0.005)	(0.0007)	.	(0.005)	.	0.0046	(0.005)	
1	IARM 154C	0.339	0.423	0.0174	0.0043	0.37	0.120	0.215	12.41	(0.0034)	0.016	0.036	0.054	0.014	0.0015	0.043	(0.004)	0.0007	.	(0.0042)	.	0.0058	(0.005)	
1	ECRM 272-1C	0.2815	0.600	0.0156	0.0196	0.420	0.0192	0.2445	11.927	0.0046	0.0145	0.0030	0.0508	0.0028	0.00096	0.0167	0.0116	0.0018	9.0	
1	IMZ C-168	0.24	1.36	0.019	0.012	1.12	0.093	0.17	13.91	(0.004)	(0.019)	0.026	(0.057)	.	(0.003)	0.053	0.009	.	
1	IARM 205D	0.232	0.736	0.0209	0.0028	0.257	0.122	0.841	12.18	0.0021	0.043	1.002	0.0484	0.013	0.0022	0.319	0.004	0.0007	(20)	0.0053	(20)	0.0047	1.07	
1	IARM 20C	0.18	0.30	0.018	0.007	0.35	0.060	1.93	12.15	(0.004)	0.031	0.12	0.0222	0.010	(0.003)	0.086	.	.	.	0.0068	.	0.004	2.59	
1	IARM 12B	0.174	0.6	0.016	0.003	0.56	0.143	2.15	16.02	(0.003)	0.018	0.057	0.061	0.011	0.003	0.037	.	(0.0003)	.	0.0101	.	0.006	0.014	
1	IMZ C-167	0.175	1.16	0.016	0.0025	0.755	0.106	0.16	13.07	(0.018)	(0.021)	0.024	0.053	.	(0.002)	0.054	0.009	.	
1	IARM Fe418-18	0.168	0.429	0.016	(0.0005)	0.32	0.22	2.00	12.4	(0.004)	0.029	0.104	0.031	(0.019)	.	0.046	.	.	.	(0.004)	.	(0.005)	2.63	
1	IARM 12C	0.155	0.55	0.022	0.0032	0.34	0.33	2.23	15.78	(0.004)	0.048	0.125	0.056	0.020	(0.002)	0.040	(0.004)	0.0004	7	(0.005)	(5)	0.008	0.015	
1	IARM 335A	0.138	0.85	0.016	0.0005	0.39	0.086	4.27	15.30	0.019	0.063	2.72	0.085	0.015	(0.002)	0.094	(0.01)	0.0007	(10)	0.0020	.	0.0034	0.008	
1	IARM Fe410-18	0.132	0.50	0.017	0.0014	0.29	0.046	0.280	12.2	(0.003)	0.012	0.146	0.046	0.0021	.	0.065	.	.	.	(0.009)	.	.	(0.008)	
1	ECRM 296-1C	0.1166	0.676	0.0178	0.0026	0.242	0.1498	2.790	11.82	0.0275	0.0218	1.700	0.0214	.	.	0.363	0.0139	(0.0003)	.	.	1.6	0.0131	.	
1	IARM 10D	0.110	1.11	0.0178	0.334	0.475	0.192	0.291	12.42	(0.0027)	0.0187	0.148	0.0241	.	0.0027	0.0015	0.051	(0.007)	(0.002)	.	(0.005)	.	0.010	(0.005)
1	IARM 291A	0.11	0.71	0.016	0.009	0.23	0.060	2.62	11.3	(0.004)	0.021	1.61	0.035	0.022	0.0011	0.29	.	0.001	.	.	0.014	.	0.004	(0.01)
1	IARM 14C	0.061	0.385	0.021	0.0015	0.63	0.19	0.364	24.9	0.0041	0.043	0.101	0.058	0.013	0.013	0.078	(0.003)	0.0005	.	(0.006)	(1)	0.004	0.031	
1	IMZ C-163A	0.058	1.38	0.018	0.010	0.39	0.061	4.59	22.62	0.018	(0.020)	2.40	0.221	0.13	(0.002)	0.029	(0.0035)	(0.003)	(0.016)	
1	JSS 670-4	0.0480	1.489	0.0201	0.0093	0.731	0.1093	0.201	11.15	0.0278	.	0.0996	
1	SRM 345b	(0.043)	0.4902	0.0176	(0.0008)	0.7821	3.000	4.054	16.03	(0.013)	0.0660	0.1541	(0.013)	0.2143	(0.007)	0.0662	(0.0031)	<0.001	.	(0.014)	(20)	0.00568	0.0394	
1	IARM 22C	0.042	0.63	0.027	0.0004	0.39	3.24	4.63	14.28	0.006	0.086	0.48	0.030	0.290	0.002	0.068	(0.004)	0.0006	(2)	0.0021	.	0.013	0.031	
1	JSS 650-15	0.0356	0.487	0.0369	0.00411	0.257	0.0311	0.215	16.11	0.00203	0.0166	0.0939	0.0446	.	.	0.0239	last	
1	IARM 355A	0.0274	0.47	0.0186	0.31	0.435	0.083	0.427	17.81	0.0016	0.047	0.337	0.0439	0.0095	0.0020	0.038	(0.004)	(0.0011)	.	(0.010)	(2)	(0.005)	(0.018)	
1	IARM 317A	0.025	1.26	0.028	0.0007	0.39	0.21	4.19	22.5	0.005	0.064	0.249	0.123	(0.004)	(0.002)	0.061	(0.006)	0.0019	(3)	0.0032	.	0.008	0.015	
1	NCS HC41318	0.023	1.25	0.030	0.0013	0.421	0.136	4.85	22.26	.	0.047	3.11	0.175	0.014	0.0014	0.038	0.0085	0.0032	0.011	
1	IARM 327A	0.018	0.54	0.018	0.0010	0.43	0.082	3.83	12.73	(0.003)	0.019	0.53	0.0157	0.008	0.0026	0.036	(0.004)	(0.001)	.	.	0.0047	.	0.006	0.009
1	IARM 14B	0.016	0.426	0.022	0.0015	0.51	0.071	0.29	23.60	0.004	0.030	0.095	0.043	0.006	0.0024	0.11	.	(0.0004)	.	0.0054	.	0.005	0.011	
1	IARMFel55PH-18	0.015	0.616	0.021	(0.0004)	0.430	3.35	4.79	15.13	0.014	0.024	0.129	0.0494	0.273	.	0.055	(0.0026)	(0.0005)	.	0.0028	.	0.0021	0.019	
1	JSS 670-3	0.008	0.53	0.020	(0.0005)	0.55	0.044	0.21	11.23	(0.005)	.	0.020	0.0064	.	0.26	

LOW NICKEL STAINLESS STEEL CHIPS

= Class, where 1 = CRM and 2 = RM C13X: typical analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Ti	V	As	B	Ce	Pb	Sn	Units
1	IMZ 1.38	1.08	1.14	0.010	0.016	0.94	0.34	0.63	19.12	.	0.021	.	.	.	0.033	0.0023	100 g
1	ECRM 278-1	0.903	0.405	0.0154	0.0052	0.336	0.077	0.236	18.11	.	.	1.040	.	.	0.077	100 g
1	IMZ 1.44	0.43	0.86	0.015	0.013	0.87	0.077	1.08	17.07	.	.	1.29	100 g
1	IRSID 201-1	0.291	0.363	.	.	0.843	0.099	0.202	12.33	.	.	0.050	100 g
1	BCS 339	0.29	0.41	0.022	0.022	0.36	(0.08)	0.37	12.40	100 g
1	BCS 469	0.279	0.598	0.015	0.020	0.421	(0.02)	0.246	11.93	(0.02)	100 g
1	BCS 472	0.227	1.02	0.032	0.029	1.05	(0.02)	1.95	15.82	.	.	0.661	.	.	(0.02)	100 g
1	IPT 26	0.201	0.713	0.022	0.012	0.306	0.029	0.413	13.69	.	.	0.070	100 g
2	C13X 150240	0.20	0.66	0.042	0.035	0.77	0.36	3.00	14.9	.	0.10	0.26	0.17	50 g
1	BCS 342	0.18	0.91	0.030	0.026	0.92	(0.08)	2.16	16.15	.	.	0.69	100 g
1	BCS 340	0.18	0.38	0.024	0.020	0.35	(0.06)	0.40	16.35	100 g
1	BCS 473	0.172	0.494	0.019	0.030	0.604	(0.03)	(0.06)	9.06	.	.	0.95	.	.	(0.02)	100 g
1	BCS 470	0.153	0.235	0.024	0.035	0.335	(0.02)	0.369	17.68	(0.02)	100 g
1	VS S32/4	0.136	0.368	0.0115	0.0141	0.338	0.152	2.97	13.73	.	.	0.050	.	.	0.205	.	.	.	W:1.82	.	100 g
1	NCS HC28318	0.134	0.456	0.027	0.0067	0.505	0.127	1.78	16.26	.	0.051	0.152	.	(0.002)	0.074	0.0064	.	.	(0.0001)	0.0058	50 g
2	C13X 147750	0.13	1.47	0.060	0.074	0.59	0.22	1.79	17.84	.	0.16	0.51	0.72	50 g
1	IMZ 1.42	0.114	0.49	0.013	0.012	1.18	0.22	0.53	17.11	0.88	.	.	.	0.16	100 g
1	VS S34/5	0.106	0.232	0.0135	0.0035	0.519	0.159	3.97	15.52	.	.	.	0.089	0.511	0.58	100 g
1	IMZ C-156	0.101	0.84	0.031	0.008	1.11	0.071	0.64	16.96	(0.034)	(0.033)	0.035	.	(0.032)	0.073	100 g
1	BCS 341	0.100	0.43	0.016</																	

STAINLESS STEEL CHIPS AND POWDER WITH NITROGEN

# = Class, where 1 = CRM and 2 = RM		analysis listed in mass % except * which is mg/kg										Cl3X: typical analysis				JK, JSS, VS S44-2: 150 g chips							NILAB: 150 g powder all others: 100 g chips			
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	As	B	Ca*	O	Pb*	Sn	W			
1	IARM 339A	0.16	1.71	0.004	0.009	0.64	0.021	12.9	17.0	0.004	0.007	2.79	0.0060	(0.005)	(0.002)	0.007	(0.001)	0.0006	14	0.016	.	(0.002)	(0.0119)			
1	IARM 289A	0.126	1.67	0.006	0.0019	0.58	0.016	7.12	17.0	0.01	0.054	(0.005)	0.0032	0.008	0.028	0.01	.	0.0003	.	0.0104	.	(0.002)	0.01			
1	IARM 241D	0.125	1.94	(0.003)	0.0023	1.00	0.242	8.98	18.12	0.022	0.022	(0.02)	(0.008)	0.028	0.018	0.031	(0.001)	0.0016	(12)	(0.005)	(3)	(0.0022)	(0.012)			
1	IMZ C-166A	0.108	1.99	0.019	0.005	2.51	0.025	21.93	25.53	0.036	0.030	(0.025)	0.077	.	0.003	0.038	(0.0026)	(0.0035)	.			
1	IMZ C-164	0.100	1.77	0.019	0.002	0.82	0.26	6.75	20.96	0.040	0.035	3.48	0.249	0.049	(0.003)	0.053	(0.005)	(0.003)	(0.025)			
1	IARM 234C	0.092	1.93	0.0090	(0.0027)	0.88	3.41	9.00	18.15	0.035	0.034	0.012	(0.01)	0.053	0.026	0.055	(0.001)	0.0023	(17)	(0.005)	(10)	0.0017	(0.006)			
1	VS S41/5	0.085	1.51	0.018	0.0069	1.41	0.155	8.85	18.65	.	.	.	0.142	.	.	2.04	(<0.005)			
1	IMZ C-165	0.082	0.98	0.017	0.007	1.42	0.040	19.01	23.28	0.038	0.029	0.025	0.105	.	(0.002)	0.042	(0.003)	0.003	.			
1	IARMPe177PH-18	0.080	0.730	0.020	(0.0005)	0.51	0.36	7.11	17.08	1.09	0.048	0.350	0.0153	0.009	0.083	0.062	.	(0.0017)	.	.	.	(0.006)	(0.011)			
1	ECRM 270-1C	0.0742	0.540	0.0196	0.0007	1.517	0.1076	10.86	20.88	(0.0023)	0.0685	0.2099	0.1417	.	(0.0019)	0.0256	(0.0034)	Ce: 0.0487	.	La: 0.0154	.	.	(0.0244)			
1	IARM 152C	0.072	0.74	0.024	0.0006	0.263	0.316	7.30	16.99	0.94	0.113	0.36	0.0172	0.012	0.098	0.072	(0.004)	0.0029	(5)	(0.001)	.	0.007	0.026			
1	IARM 316A	0.070	0.61	0.023	0.0011	1.50	0.19	10.81	21.07	0.006	0.118	0.250	0.16	(0.003)	(0.002)	0.042	0.007	Ce: 0.064	17	0.0052	(1)	0.006	0.022			
1	IARM 18D	0.069	8.1	0.032	0.0025	3.68	0.421	8.39	16.7	(0.006)	0.086	0.325	0.170	(0.031)	0.012	0.064	.	(0.0011)	.	.	.	(0.007)	(0.026)			
1	CMSI 1335	0.069	4.76	0.031	0.011	0.470	0.121	4.54	11.54	0.63	0.044	3.09	0.040	.	0.010	0.020	0.0093	.	.	.	last	0.015	0.023			
1	BAM 237-1	0.068	1.443	0.032	0.012	0.482	0.123	10.32	17.24	.	0.221	0.306	0.035	0.660	.	0.057			
1	BCS 465/1	0.066	1.380	0.021	0.012	0.405	0.098	9.24	17.31	0.026	0.053	0.092	0.010	.	0.40	0.102	.	0.0006			
1	IARM 3E	0.0553	1.62	0.0259	0.0009	0.307	0.259	11.99	22.47	0.0045	0.120	0.215	0.063	0.014	0.0022	0.126	(0.005)	(0.0005)	15	.	0.0048	(3)	0.007	0.018		
1	IARM Fe304H-18	0.052	1.82	0.031	0.027	0.298	0.460	8.35	18.4	(0.005)	0.136	0.43	0.072	(0.010)	.	0.075	0.0076	.	.	(0.008)	.	(0.014)	0.027			
1	JSS 651-16	0.0514	0.925	0.0353	0.00384	0.557	0.350	8.04	18.12	0.0017	0.217	0.278	0.0604	.	0.074			
1	IARM 253B	0.051	1.61	0.13	0.011	0.46	0.44	9.11	17.64	(0.004)	0.145	0.59	0.031	0.021	0.0027	0.092	0.0052	0.0007	.	0.007	Se: 0.13	(0.012)	(0.05)			
1	IPT 98 **	0.050	1.88	0.042	0.016	0.26	0.292	11.01	16.75	0.073	0.125	1.92	0.0112	.	0.41	0.053	0.019	0.053			
1	IARM 318B	0.050	1.02	0.022	0.0006	0.41	1.63	5.71	15.9	(0.004)	0.100	1.57	0.032	0.086	0.014	0.115	(0.004)	0.0003	.	0.009	.	0.004	0.087			
1	ECRM 269-1C	0.0499	1.262	0.0313	0.0010	0.441	0.366	8.044	18.150	.	0.1116	0.397	0.0460	0.242	0.0006	0.0991	0.0061	0.0099	0.0306			
1	IARM 8H	0.049	1.81	0.0250	(0.002)	0.40	0.192	9.08	17.14	(0.005)	0.083	0.237	0.027	0.48	0.0027	0.049	.	(0.0002)	.	(0.004)	.	(0.008)	(0.016)			
1	IARM 6i	0.049	1.76	0.0208	(0.023)	0.31	0.202	9.20	17.76	0.084	0.052	0.133	(0.013)	(0.018)	0.60	0.048	(0.005)	0.0034	.	0.0012	.	(0.0060)	(0.023)			
1	IARM 5i	0.049	1.443	0.0279	0.033	0.433	0.487	10.04	16.67	0.004	0.185	2.027	0.048	0.0133	0.0025	0.064	0.006	0.0006	(16)	0.0057	last	0.0077	0.182			
1	IPT 24A	0.048	1.53	0.035	0.020	0.510	0.32	11.12	17.37	.	(0.16)	2.47	(0.036)			
1	ECRM 281-1	0.048	0.786	0.012	0.016	0.929	0.076	9.37	18.17	.	0.023	.	0.023	.	0.216	.	.	0.0012	.	.	5	.	.			
1	IARM 4F	0.047	1.17	0.0195	0.0015	0.494	0.146	20.1	24.5	0.015	0.067	0.142	0.056	0.007	0.0031	0.146	(0.003)	(0.0012)	(20)	(0.004)	.	(0.005)	0.012			
1	IARM Fe303-18	0.046	1.55	0.033	0.35	0.47	0.61	8.12	17.2	.	0.140	0.42	0.069	0.015	.	0.072	0.007	(0.0012)	.	(0.006)	.	(0.015)	0.029			
1	JSS 651-14	0.046	1.19	0.027	0.0058	0.67	0.12	9.03	18.26	(0.002)	0.17	0.11	(0.0426)	last of stock	.			
1	IARM 4G	0.0454	1.36	0.027	0.0008	0.630	0.320	19.2	24.9	0.008	0.085	0.580	0.058	0.008	0.029	0.092	(0.005)	0.0032	(10)	(0.003)	(5)	0.008	0.017			
1	IARM 6J	0.045	1.52	0.028	(0.002)	0.62	0.383	9.00	17.74	0.0195	0.191	0.387	0.0109	0.010	0.34	0.081	.	0.0024	.	(0.001)	.	(0.009)	0.026			
1	JSS 655-10	0.045	0.96	0.024	(0.0005)	0.63	0.045	9.75	17.53	(0.003)	(0.073)	0.033	0.0072	0.49			
1	IARM 4E	0.044	1.07	0.0224	(0.0006)	0.514	0.234	20.18	24.25	0.004	0.066	0.32	0.0028	0.024	Ta: 0.005	0.052	(0.005)	0.0011	.	0.0021	.	0.0060	0.046			
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	As	B	Ca*	O	Pb*	Sn	W			
1	IARM 8i	0.0424	1.395	0.0352	0.0118	0.38	0.441	9.01	17.08	(0.0030)	0.301	0.416	0.052	0.60	(0.008)	0.057	.	(0.0005)	.	(0.004)	.	(0.012)	0.060			
1	IARM 8G	0.042	1.468	0.0327	0.0126	0.36	0.390	9.02	17.20	0.0030	0.162	0.359	0.046	0.53	0.0024	0.062	(0.007)	(0.0005)	(5)	(0.003)	.	0.0107	0.032			
1	IARM 17D	0.041	4.15	0.026	0.0018	0.416	0.412	11.83	21.06	0.0032	0.23	1.52	0.311	0.14	0.010	0.118	0.005	0.001	(20)	0.003	(2)	0.0044	0.056			
1	NILAB 500HAC	0.041	1.541	0.024	0.012	0.720	0.182	11.00	16.93	.	0.139	2.73	0.1154	0.023	.	0.074			
1	IARM 253A ***	0.041	1.50	0.140	0.0089	0.50	0.223	9.17	17.90	0.003	0.088	0.348	0.0373	0.016	0.002	0.106	.	0.0003	.	0.009	.	0.01	0.10			
1	IARM 6G	0.040	1.39	0.030	0.0006	0.37	0.41	9.14	17.15	0.030	0.150	0.330	0.011	0.013	0.440	0.089	.	0.0004	.	0.0017	.	0.014	0.033			
1	JSS 653-16	0.0387	1.426	0.0252	0.00034	0.610	0.106	14.26	23.18	0.022	0.167	0.119	0.0384	.	.	0.071			
1	JSS 652-16	0.0369	0.938	0.0327	0.00148	0.628	0.272	10.06	16.80	0.0022	0.209	2.06	0.0224	.	.	0.089			
1	ECRM 292-1C	0.0367	1.744	0.0175	0.0055	0.402	0.0391	10.09	18.00	(0.002)	0.0255	0.0464	0.0640	0.571	.	.	(0.008)	.	(6)			
1	IARM 21D	0.032	0.052	0.008	(0.0014)	0.039	0.017	8.29	12.69	1.03	0.078	2.23	0.0037	(0.005)	0.016	0.017	(0.012)			
1	IARM 15C	0.032	0.760	0.019	0.0018	0.26	1.54	6.35	14.39	(0.005)	0.024	0.722	0.0148	0.63	(0.002)	0.041	0.0044	(0.0006)	.	(0.003)	(0.003)	0.009	(0.020)			
1	IARM FeN50-18	0.030	5.27	0.026	(0.0013)	0.24	0.28	11.90	21.0	(0.006)	0.081	2.01	0.26	0.18	(0.002)	0.121	.	.	.	(0.006)	.	(0.007)	0.023			
1	IARM 162D	0.0240	1.82	0.0296	0.0271	0.570	0.52	8.15	18.31	(0.0026)	0.074	0.573	0.097	0.0090	0.013	0.063	0.0072	0.0027	(30)	0.005	.	0.0102	0.028			
2	TL 2001C	0.0244	0.679	0.022	0.0006	0.27	0.612	7.5	25.58	.	0.046	3.49	0.279	0.024	.	0.079	0.57			
1	IARM Fe304L-18	0.024	1.39	0.034	0.029	0.43	0.54	8.17	18.34	(0.003)	0.156	0.462	0.081	0.013	0.0056	0.076	0.007	(0.0012)	.	(0.006)	.	(0.013)	0.056			
1	ECRM 297-1C	0.0223	0.897	0.0137	0.0101	0.344	0.204	12.33	18.37	0.0195	0.0413	0.290	0.0152	(0.0089)	0.0072	0.0535	0.0040	1.146	(2)	.	.	.	(0.0057)			
1	IARM Fe316L18	0.021	1.70	0.033	0.029	0.438	0.550	10.12	16.7	(0.006)	0.209	2.02	0.067	(0.027)	(0.003)	(0.067)	.	.	.	(0.005)	.	(0.013)	(0.06)			
1	IARM 301B	0.0206	0.807	0.0251	0.0010	0.419	0.192	7.12	25.06	0.005	0.055	3.75	0.297	0.020	(0.003)	0.070	(0.004)	0.0024	(9)	0.0069	(3)	0.0051	0.050			
1	ECRM 284-2C	0.0201	1.745	0.0258	0.0237	0.537	0.1831	10.72	16.811	0.0027	0.0525	2.111	0.0151	.	0.191	0.0425	0.0063	0.0026	.	0.0099	.	0.0047	.			
1	BCS 463/1	0.019	1.400	0.0025	0.019	0.270																				

STAINLESS STEEL CHIPS AND POWDER

= Class, where 1 = CRM and 2 = RM

Cl3X: typical analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Ti	V	As	B	Ce	Pb	Sn	Units	
1	IMZ 1.45	0.34	0.84	0.028	0.012	2.67	0.38	5.23	27.89	.	.	0.59	100 g	
1	VS S30/4	0.293	0.510	0.0117	0.0053	2.51	.	6.39	12.74	.	.	.	0.060	100 g	
1	BCS 468/1	0.143	1.70	0.014	0.020	1.41	.	8.90	17.96	.	0.018	100 g	
1	NCS HC28315	0.110	0.841	0.024	0.0082	0.780	0.089	18.02	23.71	0.0056	0.102	0.115	0.016	(0.003)	0.077	0.0042	.	.	0.0004	0.0025	50 g	
1	BCS 462	0.092	0.74	0.010	0.018	0.46	.	12.55	12.35	0.0005	.	100 g last of stock
2	Cl3X 190030	0.09	1.60	0.063	0.029	0.59	0.08	13.1	18.9	.	.	2.50	0.11	50 g
2	Cl3X 180040	0.09	1.53	0.077	0.017	1.30	0.02	11.98	21.84	.	0.16	0.60	0.78	50 g
1	BCS 463	0.088	0.77	0.015	0.017	0.51	.	9.65	18.29	(0.0004)	100 g
1	ECRM 282-1	0.086	1.64	0.019	0.0042	0.734	0.109	10.86	16.72	.	.	2.19	.	0.488	100 g
1	IMZ 1.12/4	0.084	1.47	0.040	0.013	0.30	.	10.14	17.41	.	.	1.96	.	0.52	100 g
1	NM 220	0.084	1.35	(0.030)	0.013	0.56	0.12	8.70	19.26	.	0.16	100 g
1	DSZU CX06	0.082	1.20	0.026	0.0118	0.64	0.16	10.23	18.40	(0.1)	(0.04)	(0.13)	.	0.56	(0.03)	(0.01)	100 g
1	IMZ C-154	0.076	2.18	0.040	0.16	0.89	0.33	9.86	17.71	(0.16)	0.105	2.58	.	1.00	0.073	100 g
1	VS S62	0.071	0.064	(<0.001)	0.0128	0.032	0.0083	13.00	17.24	(0.02)	.	.	.	0.030	.	.	Ca:0.058	O:(0.35)	.	.	.	100 g powder
2	Cl3X 190020	0.07	1.05	0.031	0.053	0.105	0.105	9.18	17.1	.	.	1.99	0.07	50 g
1	NCS HC28316	0.067	1.10	0.028	0.021	0.435	0.166	10.39	16.80	0.012	0.063	2.01	0.027	(0.006)	0.048	0.0037	.	.	0.0005	0.0034	50 g	
1	IMZ C-152	0.065	1.42	0.010	0.0025	0.52	0.061	9.48	18.04	.	.	0.017	.	.	0.030	100 g
1	BCS 332	0.063	0.80	0.015	0.020	0.44	(0.10)	12.45	12.80	.	(0.037)	.	.	.	(0.02)	100 g
1	BCS 333	0.066	0.79	0.016	0.020	0.45	.	9.49	18.7	100 g
1	VS S43/4	0.058	0.408	0.0153	0.0048	0.717	0.122	10.20	19.69	.	.	5.02	0.78	0.686	.	(0.004)	100 g
1	VS S38/6	0.056	1.60	0.0135	0.0030	0.970	0.096	8.47	17.06	0.445	100 g
1	IRSID 202-1	0.055	.	.	.	0.68	.	9.8	16.	.	.	2.30	.	0.54	100 g last of stock
1	IMZ 1.40	0.054	1.60	0.011	0.017	0.93	0.098	16.10	17.59	.	.	3.70	.	0.47	100 g
1	NCS HC41317	0.053	1.03	0.032	0.00071	0.571	0.383	9.19	17.17	.	0.132	0.154	0.0095	0.309	0.059	0.0047	.	.	W:0.018	0.013	50 g	
1	SRM 339	0.052	0.738	0.129	0.013	0.654	0.199	8.89	17.42	.	0.096	0.248	.	.	0.058	Se:0.247	.	150 g
1	SRM 1155	0.0445	1.619	0.0200	0.0175*	0.5093	0.1734	12.35*	18.37*	.	0.1052	2.386	.	.	0.0508	*	Wide Uncertainties	(0.001)	.	.	.	150 g
1	NCS HC28313	0.039	1.07	0.037	0.016	0.425	0.399	8.19	18.31	.	0.208	0.027	.	(0.002)	0.106	0.0035	.	.	(0.0001)	0.0051	50 g	
1	VS S39/4	0.037	0.97	0.0092	0.0048	0.526	0.019	9.91	18.04	Se:0.213	.	100 g
1	BCS 462/1	0.0345	0.722	0.0053	0.0041	0.463	0.0112	12.85	11.8	.	.	0.0304	100 g
1	NCS HC28314	0.021	0.940	0.034	0.0028	0.414	0.043	8.11	18.21	.	0.216	0.025	.	0.006	0.089	0.0025	.	.	(0.0001)	(0.0001)	50 g	
1	VS S37/5	0.018	1.43	0.0067	0.0079	0.696	0.133	12.28	17.39	.	0.0069	.	1.03	100 g
1	NCS HC28317	0.018	1.17	0.042	0.0057	0.317	0.334	10.34	16.61	.	0.185	2.05	.	(0.002)	0.070	0.0055	.	.	(0.0001)	0.0073	50 g	
1	VS S29/4	0.017	0.636	0.0099	0.0026	0.751	0.018	19.02	11.39	0.149	.	0.018	.	2.88	0.0099	Sb:0.00027	.	.	0.00017	0.0006	100 g Zn: 0.0017	
1	SRM 101g	0.0136	0.085	0.007	0.0078	1.08	0.029	10.00	18.46	.	0.09	(0.004)	.	.	0.041	(0.003)	100 g
1	NCS HC28320	0.013	1.17	0.033	0.0021	0.464	1.49	24.23	19.67	0.024	0.096	4.47	0.042	(0.002)	0.086	0.0053	.	.	(0.0001)	0.0043	50 g	
1	BCS 461/1	0.0103	0.686	0.0053	0.0051	0.374	0.0091	6.124	14.727	.	(0.004)	0.0138	100 g
1	IARM 99D	(0.006)	(0.013)	(0.004)	0.0011	(0.03)	(0.045)	18.4	(0.12)	0.117	9.24	4.8	(0.011)	0.67	(0.037)	.	0.0026	.	(0.010)	.	.	100 g
1	JK 25	.	(1.7)	(11.3)	(22.3)	.	.	(0.1)	0.096	.	.	.	150 g
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Ti	V	As	B	Ce	Pb	Sn	Units	

HIGH ALLOY STEEL CHIPS AND POWDER

= Class, where 1 = CRM and 2 = RM

C13X: typical analysis 50 g chips

CMSI, JSS, JK, and SRM 126c: 150 g chips

NILAB: 150 g powder

all others: 100 g chips

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn	Other	
1	IMZ 1.39	0.23	1.75	0.022	0.009	1.96	.	35.23	15.57	
1	BAM 327-2	0.152	1.289	0.0228	0.0046	2.052	0.060	19.72	24.35	0.070	0.159	0.174	0.059	.	.	0.044	
1	ECRM 286-1	0.100	1.92	0.026	0.280	.	.	8.55	18.13	.	0.150	0.329	0.043	0.0084	Sb: 0.0014	
1	BCS 464/1	0.086	0.791	0.020	0.028	0.57	.	20.05	25.39	.	0.054	(0.003)	.	.	.	0.0004	.	.	
1	BCS 467/1	0.082	0.788	0.018	0.019	0.52	.	9.21	18.09	0.99	.	.	.	0.004	.	.	0.004	.	.	
2	C13X 142110	0.08	0.70	0.006	0.016	1.72	0.31	12.4	26.05	.	0.08	0.30	.	0.18	.	.	3.29	
1	NCS HC41503	0.071	0.807	0.015	0.0006	0.36	0.038	32.27	20.72	0.299	0.050	0.297	.	.	0.49	
1	VS S55/2	0.059	0.476	0.0095	0.0030	0.357	.	0.416	8.34	.	35.05	6.46	
1	IARM 24B	0.053	0.82	0.009	0.0010	0.28	0.052	35.86	0.121	0.002	0.036	0.011	0.0017	<0.01	0.002	<0.005	<0.04	<0.005	(0.001)	0.003	.	0.0018	Se: 0.19	
1	BCS 479	0.0529	0.680	0.0029	0.0030	0.553	0.0052	24.87	19.922	(0.013)	(0.002)	(0.003)	0.0057	0.625	0.0306	0.0052	.	(0.002)	<0.0005	
1	BCS 475	0.050	0.89	0.037	0.008	0.21	1.94	5.66	14.14	0.013	0.22	1.59	.	0.22	0.015	
1	ECRM 289-1C	0.0489	1.016	0.0114	0.0027	0.531	.	24.68	14.63	0.199	0.065	1.102	.	.	2.01	0.260	.	.	0.0044	.	.	.	0.111	
1	IARM 15B	0.047	0.39	0.013	0.001	0.33	1.53	6.94	14.53	0.006	0.24	0.82	0.0355	0.65	0.005	0.033	0.12	.	.	0.0039	.	.	0.009	
1	IARM 26D	0.038	0.224	0.013	(0.0008)	(0.05)	0.047	24.6	14.29	0.29	0.040	1.23	0.0035	(0.007)	2.17	0.223	0.036	.	0.0063	.	.	.	0.0039	
1	VS S47/4	0.036	0.402	0.0062	0.0083	0.366	0.686	30.84	.	.	4.06	
1	ECRM 273-1	0.0336	0.785	0.0131	0.0004	0.378	3.046	4.85	14.747	.	0.0391	0.2462	0.0444	0.221	.	0.0512	.	0.0030	0.0021	
1	CMSI 1320	0.032	0.578	0.013	0.0036	0.238	0.030	22.43	4.04	0.0024	0.011	0.0019	(0.011)	.	0.0018	0.0047	(0.001)	0.0026	0.0022	
1	SRM 126c	0.02540	0.4684	(0.00350)	(0.0050)	0.1936	(0.0396)	36.054	(0.0625)	.	(0.0080)	(0.0110)	.	.	.	(0.001)	
1	IARM 302B	0.0226	0.93	0.0256	0.0007	0.56	0.701	17.7	20.33	0.0159	0.072	6.24	0.180	0.012	0.0031	0.052	0.025	(0.009)	0.0027	0.0032	(0.001)	0.0075	Ta: 0.004	
1	IARM 153C	0.0225	1.60	0.0289	0.0288	0.349	0.442	11.10	18.22	(0.003)	0.251	3.00	0.086	0.015	0.004	0.058	0.043	0.0061	0.0009	0.006	(0.001)	0.010	.	
1	BCS 474	0.022	1.70	0.008	0.020	0.17	0.35	14.74	19.06	.	(0.02)	3.55	.	.	.	0.30	.	0.030	
1	SRM 868	0.022	0.052	<0.003	0.0025	0.097	0.022	37.78	0.077	0.99	16.1	0.014	.	2.99	1.48	0.077	.	.	0.0078	
1	VS S33/4	0.020	0.733	0.0095	0.0058	0.354	.	22.48	15.25	1.38	.	4.38	.	0.0079	
1	VS S64	0.017	0.147	0.0023	0.0037	0.267	0.044	33.20	0.146	.	16.57	
1	ECRM 295-1C *	0.0166	1.758	0.0167	0.0004	0.418	1.481	24.40	19.51	0.0203	0.0450	3.996	0.0615	.	.	0.0453	.	0.0041	0.0018	.	.	.	0.0025	*
1	IARM 157D	0.0154	0.626	0.016	0.0005	0.28	0.196	23.9	20.31	0.020	0.102	6.08	0.203	0.149	0.009	0.050	0.036	.	0.0007	.	.	.	0.0036	Fe: 48.0
1	ECRM 299-1C	0.0154	0.2678	0.0152	0.00022	0.299	0.0382	0.172	22.32	5.33	0.0187	0.0186	0.0198	.	0.1289	0.0329	.	0.0054	0.0002	Zr: 0.1775
1	IARM 153B	0.015	1.58	0.031	0.0082	0.28	0.408	13.19	18.13	0.006	0.115	3.12	0.0158	0.008	0.002	0.031	0.020	.	0.0022	0.0052	.	.	0.014	
1	ECRM 298-1C	0.0146	0.398	0.0198	0.0006	0.262	0.201	7.056	24.72	0.0285	0.055	3.799	0.263	.	0.0014	0.0607	.	.	0.0021	.	.	0.00008	.	Fe: 63.38
1	NILAB 501HAC	0.014	0.858	0.020	0.003	.	0.761	17.69	19.79	0.003	0.159	6.14	0.2243	0.007	.	0.044	
1	VS S42/4	0.014	0.604	0.0105	0.0049	0.958	2.85	26.43	23.30	0.0140	.	2.68	.	.	0.270	
1	VS S66	0.0124	0.0270	.	0.0054	0.050	3.30	28.28	17.54	.	.	1.78	.	.	0.486	Ca:0.202	.	.	.	
1	ECRM 379-1D	0.0121	1.804	0.0166	0.0006	0.393	0.984	30.83	26.79	(0.00246)	0.0390	3.290	0.0550	(0.0028)	(0.0014)	0.0663	(0.0091)	(0.0018)	0.00190	(0.0027)	(0.000038)	0.0021	Sb: 0.00057	
1	VS S46/5	0.01	0.4	0.002	0.003	0.1	.	29.3	.	.	17.2	
2	DH E2401	0.0048	0.0203	0.0013	0.0026	0.0222	0.0161	18.85	0.0405	.	11.46	4.64	Ca:0.0002	0.0023	1.28	0.0029	.	0.0038	.	Sb:0.0003	<0.0001	0.0016	Al.s:0.1013	
1	VS S65	0.0031	0.275	0.0201	0.0119	0.017	0.469	29.63	0.236	.	13.94	
1	VS S63	0.0024	0.402	0.0166	0.0113	0.175	0.284	27.73	0.016	.	18.63	
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn	Other	

* ECRM 295-1C also contains Fe: 48.36, Mg: (0.0003), and Sb: 0.0007

** Provisional Analysis

CAST IRON CHIPS WITH GRAPHITIC CARBON

analysis listed in mass %

IPT: 80 g

SRM: 150 g

all others: 100 g

Number	C	C.Grph	Mn	P	S	Si	Cu	Ni	Cr	Mo	Ti	V	As	Sn	Mg	N
IPT 75A	3.4	2.7	0.722	0.250	0.033	1.98	0.433	0.425	0.487	0.438	0.022	0.030
IPT 69	3.34	2.50	0.715	0.267	0.018	2.07	0.47	0.272	0.353	(0.004)	0.019
IPT 37B	3.37	2.85	0.737	0.148	0.069	1.66	0.052	0.074	0.088	.	0.034
SRM 4L	3.21	2.66	0.82	0.149	0.043	1.33	0.240	0.042	0.118	0.040	.	0.024
NM 73 **	3.07	2.55	0.82	0.22	0.014	1.21	.	** Combined	Carbon: 0.52%
VS Ch15/1	3.04	(0.2)	1.08	0.211	0.040	1.49	0.606	0.256	2.04	.	0.70	.	(0.006)	.	.	.
VS Ch6/11	3.01	(1.0)	0.776	0.289	0.031	2.38	.	0.79	0.261	0.318	0.028	.	Co:0.048	.	.	.
SRM 107c	2.99	1.98	0.480	0.079	0.059	1.21	0.205	2.20	0.693	0.83	(0.019)	(0.015)
VS Ch1/9	2.94	(2.1)	0.271	0.0125	0.0290	0.293	.	0.061	.	.	0.046	.	(0.004)	.	.	.
DSZU CH02X	2.90	(1.5)	1.08	0.006	0.013	1.36	(0.04)	0.66	0.59	0.23	0.16	.	.	(0.015)	.	.
SRM 6g	2.85	2.01	1.05	0.557	0.124	1.05	0.502	0.135	0.370	0.035	0.059	0.056	(0.042)	.	.	0.005
VS Ch19	2.73	1.73	0.250	0.074	0.028	0.202	.	0.081	0.067	.	0.038	.	0.0125	.	.	.
SRM 115a	2.62	1.96	1.00	0.086	0.064	2.13	5.52	14.49	1.98	0.050	0.020	0.014
ECRM 454-1	(2.53)	(1.96)	1.16	0.046	0.068	2.00	(0.07)	(0.21)	.	.	0.052	.	(0.025)	.	.	.
ECRM 483-1	2.46	1.65	0.596	0.615	0.103	1.75	.	.	0.039	0.130	.	.
ECRM 453-1	(2.44)	(2.37)	0.72	1.63	0.049	3.17	0.10	0.068	0.053	.	(0.040)	0.050	0.019	.	.	.
VS Ch5/7	2.27	1.02	1.27	0.0115	0.0044	1.86	0.069	0.061	0.327	.	.	.	(0.005)	.	.	0.042
SRM 342a	1.86	1.37	0.274	0.018	0.00214	2.73	0.134	0.058	0.033	0.005	0.020	0.070
SRM 341	1.81	1.23	0.92	0.024	0.007	2.44	0.152	20.32	1.98	0.010	0.018	0.012	.	.	.	0.068
VS Ch17/1	1.66	(0.8)	1.32	0.0313	0.0087	2.08	0.0197	0.039	0.299	.	.	.	(0.002)	.	.	0.044

CRM CAST IRON CHIPS

Number	C	Mn	P	S	Si	As	Units
JSS 102-9	4.59	0.265	0.125	0.0168	0.933	.	150 g
NCS HC18009	3.83	0.74	0.186	0.023	1.88	0.025	100 g
NCS HC16023	3.8	0.929	0.171	0.016	1.42	.	150 g
NCS HC11003	3.77	0.659	0.230	0.129	1.47	.	100 g
NCS HC37034	3.73	0.565	0.117	0.067	2.58	.	100 g
NCS HC37011	3.73	0.565	0.117	0.067	2.58	.	100 g
NCS HC18010	3.66	0.59	0.145	0.041	2.399	0.036	100 g
NCS HC37010	3.63	0.762	0.187	0.070	2.82	.	80 g
NCS HC16024	3.59	0.514	0.315	0.033	1.96	.	150 g
NCS HC18011	3.43	0.729	0.079	0.0082	1.93	0.036	100 g
NCS HC18013	3.40	0.79	0.049	0.0087	2.12	0.013	100 g
NCS HC18014	3.36	0.792	0.049	0.0087	2.136	0.012	100 g
NCS HC11003a	3.36	0.561	0.166	0.176	1.39	.	100 g
NCS HC11003b	3.36	0.386	0.135	0.154	1.82	.	100 g
NCS HC18012	3.23	0.74	0.079	0.0080	1.93	0.037	100 g
NCS HC16026	3.22	0.726	0.085	0.059	2.25	.	150 g
NCS HC18016	3.20	0.42	0.104	0.0092	2.91	0.092	100 g
NCS HC18003	3.18	0.732	0.243	0.049	1.43	0.064	100 g
NCS HC11006	3.11	0.850	0.270	0.130	1.37	.	100 g
NM 18A	3.06	0.43	0.05	0.11	2.67	.	100 g
NCS HC13016	2.99	1.30	0.278	0.100	1.29	.	150 g
NCS HC39003	2.95	0.26	0.142	0.085	1.49	.	100 g
NCS HC18005	2.89	0.733	0.108	0.0058	2.01	0.091	100 g
NCS HC39001	2.85	0.38	0.081	0.096	2.48	.	100 g
NCS HC16022	2.83	0.721	0.094	0.067	2.19	.	100 g
NCS HC39002	2.81	0.57	0.062	0.134	1.71	.	100 g
NCS HC39004	2.78	0.78	0.066	0.082	2.17	.	100 g
NCS HC11004	2.72	0.359	0.124	0.115	2.56	.	100 g
NCS HC18002	2.67	1.36	0.051	0.031	2.94	.	150 g
NCS HC18006	2.65	0.75	0.114	0.0057	1.99	0.092	100 g
NCS HC39010	2.65	0.331	0.113	0.134	1.29	.	100 g
NCS HC39008	2.59	0.859	0.187	0.093	2.17	.	100 g
NCS HC15011	2.58	1.00	0.087	0.068	2.76	.	100 g
NCS HC13015	2.51	0.62	0.104	0.020	4.08	.	150 g
CTIF FG20	2.487	0.571	1.440	0.109	1.726	.	100 g
NCS HC39009	2.47	1.56	0.318	0.057	3.33	.	100 g
CTIF FG10	2.322	1.098	0.111	0.016	2.467	.	100 g
NCS HC11005	2.19	0.219	0.047	0.048	3.07	.	100 g

Number	C	Mn	P	S	Si	As	Units
--------	---	----	---	---	----	----	-------

CRM CAST IRON CHIPS WITH MAGNESIUM AND RARE EARTHS

unit sizes have been abbreviated as follows: A = 80 g, B = 100 g, and C = 150 g

Number	C	Mg	T.RE	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	As	Ce	La	Sn	Units	Other
ECRM 481-1	3.91	0.051	.	0.448	0.019	0.004	2.29	0.150	1.19	0.063	0.023	.	.	0.011	.	.	0.010	.	.	.	B	
GBW 01119a	3.67	0.023	0.0187	0.497	0.084	0.0053	2.673	0.033	0.011	0.0115	.	.	0.0065	0.0013	0.068	0.0205	A	last of stock
NCS HC18011	3.43	0.030	.	0.729	0.079	0.0082	1.93	0.036	.	.	.	B	Re: 0.024
NCS HC37019	3.06	0.054	0.049	6.72	0.11	0.0041	5.80	A	
BS CE207 *	3.05	0.003	.	1.20	0.090	0.016	2.07	0.222	0.048	0.039	0.005	.	0.031	(0.001)	0.079	0.034	0.004	0.016	0.004	.	C	
ECRM 480-1	3.029	0.0172	.	0.1514	0.0021	0.0086	2.407	(0.0052)	0.4826	.	0.0163	B	
NCS HC28054	3.01	0.047	.	0.645	0.188	0.011	2.03	.	1.19	0.619	.	.	.	0.355	B	Nb: 0.095
NCS HC37020	2.88	0.068	0.047	6.40	0.11	0.0035	3.75	A	
NCS HC37021	2.79	0.028	0.045	8.77	0.10	0.0060	6.58	A	
NCS HC37018	2.78	0.049	0.041	6.80	0.12	0.0027	5.96	A	
NCS HC19017	2.77	0.070	0.070	0.570	0.015	0.014	2.52	0.046	0.031	0.042	.	.	0.037	.	0.072	0.356	B	
NCS HC11015	2.74	0.012	0.036	0.473	0.022	0.0009	2.32	0.031	0.627	0.040	.	0.021	0.011	0.0016	0.015	0.031	0.011	0.019	0.013	0.0037	A	N: 0.0047
NCS HC19018	2.70	0.083	0.083	0.625	0.024	0.011	3.10	0.049	0.031	0.043	.	.	0.035	.	0.125	0.405	B	
NCS HC19010	2.69	0.028	0.040	0.79	0.029	0.023	2.92	0.042	0.025	0.227	.	.	.	0.0016	0.109	0.236	B	
BS CE206 *	2.64	0.0006	.	0.99	0.145	0.018	2.76	0.45	0.048	0.068	0.004	.	0.029	0.007	0.078	0.038	0.004	0.011	0.004	.	C	
NCS HC37008	2.59	0.014	0.011	0.373	0.042	0.012	3.08	0.288	0.514	A	
CKD 230 *	2.55	0.040	.	0.31	0.049	0.024	1.04	1.05	1.11	0.09	.	0.01	0.01	0.05	0.01	0.02	0.005	0.01	(0.005)	0.010	B	Sb: 0.006
BS CE209 *	(2.47)	0.0013	.	0.39	0.167	0.027	2.13	0.211	0.045	0.010	0.006	.	0.030	(0.001)	0.062	0.030	0.003	0.026	0.008	.	C	
BS CE208 *	2.41	0.0008	.	0.34	0.118	0.041	1.63	0.212	0.047	0.007	0.003	.	0.031	(0.001)	0.048	0.024	0.004	0.018	0.007	.	C	
NCS HC19016	2.21	0.099	0.099	0.420	0.014	0.012	3.78	0.047	0.032	0.040	.	.	0.037	.	0.066	0.310	B	
NCS HC37005	1.92	0.073	0.059	0.955	0.041	0.0064	3.36	0.181	0.128	A	
Number	C	Mg	T.RE	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	As	Ce	La	Sn	Units	Other

* Clearance Sale Item

ALLOYED CAST IRON

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Als	Co	Mo	Ti	V	W	As	B	Bi	Pb	Sb	Sn	Units	Other
CRM																						
CMSI 1571	3.95	0.27	0.130	0.233	1.30	0.011	0.029	4.31	.	.	0.36	0.016	0.012	100 g	
NCS HC37001	3.40	0.99	0.060	0.054	1.35	1.22	0.63	13.54	.	.	1.03	50 g	
NCS HC13010	3.35	0.699	0.147	0.045	2.44	0.018	0.300	0.96	.	.	2.39	100 g	
SRM 892	3.33	0.76	0.054	0.015	1.83	0.270	5.53	10.18	.	0.31	0.20	.	0.041	150 g	
NCS HC13011	3.23	1.20	0.310	0.045	4.30	0.243	0.919	1.36	.	.	0.639	100 g	
CKD 227 *	3.2	0.95	0.66	0.037	1.67	0.33	0.05	0.68	0.04	0.03	0.60	0.07	0.11	0.06	0.01	0.007	0.0005	0.001	0.03	0.07	100 g	Zn: 0.01
NCS HC28034	3.15	0.795	0.321	0.082	1.67	1.04	.	0.464	.	.	0.515	0.053	150 g	
NCS HC37003	2.95	1.72	0.062	0.034	1.32	1.06	1.05	15.39	.	.	1.12	50 g	
ECRM 479-1	2.86	0.136	0.0764	0.0893	2.018	(0.0065)	1.0123	1.001	.	.	0.1959	100 g	Al: 0.0143
CMSI 1569	2.86	1.07	0.058	0.028	0.36	0.42	0.25	22.52	.	.	1.14	0.005	0.039	100 g	
ECRM 482-2	2.599	0.728	0.0974	0.0491	1.815	1.231	2.284	0.675	.	.	0.454	100 g	
CMSI 1568	2.46	1.63	0.383	0.013	0.32	0.73	1.20	12.95	.	.	0.76	0.0089	0.026	100 g	
NCS HC37002a	2.42	0.71	0.058	0.064	1.05	0.90	0.23	8.93	.	.	1.74	80 g	
NCS HC11013	2.35	1.05	0.010	0.0094	1.05	.	.	15.06	.	.	2.84	0.062	0.16	100 g	
CMSI 1570	2.31	0.83	0.064	0.043	0.59	0.36	0.49	26.50	.	.	2.71	0.0051	0.039	100 g	
CMSI 1308	2.223	0.142	0.0226	0.0094	0.171	0.41	0.095	12.18	.	.	0.0067	.	0.030	0.028	150 g	
ECRM 451-2	2.059	1.079	0.0593	0.0315	2.092	6.26	14.01	1.097	100 g	
CTIF FA10	1.976	1.063	0.045	.	1.480	0.492	20.05	1.986	100 g	
NCS HC11012	1.95	0.926	0.0084	0.0079	0.59	.	.	13.11	.	.	0.52	0.064	0.137	100 g	
VS Ch18	1.91	4.27	0.095	0.0147	1.167	0.257	0.168	15.61	100 g	
CTIF FA20	0.643	0.368	0.045	.	1.519	.	.	28.30	100 g	
RM																						
BS CE 216 *	.	0.80	0.193	0.043	2.60	0.68	0.24	0.41	.	0.014	0.68	0.097	0.032	.	0.0070	.	.	.	0.00043	.	150 g	
BS CE 217 *	.	1.07	0.356	0.029	3.15	0.13	0.002	1.08	.	0.014	0.002	0.093	0.036	0.00041	.	150 g	
BS CE 219 *	.	1.23	0.505	0.038	2.47	0.415	0.228	0.31	.	0.014	0.283	0.080	0.034	0.00050	.	150 g	
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Als	Co	Mo	Ti	V	W	As	B	Bi	Pb	Sb	Sn	Units	Other

* BS and CKD Clearance Sale Items, BS CE items have no uncertainties

CAST IRON CHIPS AND POWDER WITH CARBON OVER 3%

unit sizes have been abbreviated so that: A = CRM, 100g and B = CRM, 150g and C = RM, 50g

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Ti	V	As	B	Cd	Ga	Pb	Sb	Sn	Tl	Units
ECRM 490-1	4.813	10.83	0.0267	0.0040	(0.03)	0.0088	(0.02)	0.0183	.	.	0.0030	0.0035	0.0152	A
VS Ch12/2	4.33	0.968	0.051	0.0101	2.82	(<0.005)	powder
VS Ch13/1	4.16	1.11	0.067	0.034	2.90	0.91	0.454	1.30	.	1.16	.	.	.	(<0.002)	powder
JSS 110-13	4.13	0.217	0.082	0.0120	1.90	0.0042	0.0133	0.0197	.	.	0.0045	0.044	0.0126	0.0019	A
NCS HC16027	4.06	0.094	0.038	0.029	0.725	0.0023	0.0023	0.010	0.038	0.0027	.	0.026	0.0064	0.0011	.	.	.	<0.0002	0.00013	0.00014	.	A
ECRM 478-2	4.003	0.321	0.201	0.0460	2.411	0.1276	0.151	0.251	.	.	0.0023	0.0328	0.0113	(0.0018)	0.0006	A
NCS HC16028	4.00	0.634	0.046	0.0073	1.55	0.0051	0.0045	0.036	.	0.0089	.	0.084	0.018	0.0012	.	.	.	<0.0002	0.00016	0.00018	.	A
ECRM 488-2	3.956	0.201	0.0111	0.1173	0.374	0.0256	0.1247	0.303	.	.	0.0052	0.0636	0.0545	0.0013	.	A
NCS HC16010b	3.90	0.414	0.044	0.044	0.93	0.010	0.024	A
BGS 527	3.873	0.316	0.1269	0.0366	1.000	0.0104	0.0229	0.0187	A
VS Ch14/2	3.81	1.05	0.061	0.034	2.09	0.427	1.52	0.724	0.265	0.625	.	.	.	(<0.005)	powder
VS Ch2/7	3.61	0.079	0.078	0.071	0.836	0.142	0.222	0.218	0.124	0.444	.	0.293	0.521	(<0.002)	powder
NCS HC28015	3.58	0.97	0.080	0.014	3.02	0.091	0.0125	0.0075	B
ECRM 487-2 *	3.5730	0.0491	0.0065	0.0031	0.0898	0.0136	0.0219	0.0248	0.0151	0.0034	0.004	0.0022	0.0117	0.0045	A
CTIF FB20-2	3.557	(0.39)	(0.07)	0.0614	(0.935)	.	.	(0.10)	A
CTIF FB20-1	3.552	(0.39)	(0.07)	0.059	(0.935)	.	.	(0.10)	A
CMSI 1503B	3.53	1.10	0.066	0.048	1.83	0.258	0.025	A
SRM 122i	3.47	0.530	0.28	0.087	0.89	0.033	0.047	0.151	.	0.008	.	0.024	0.012	B
CMSI 1572	3.46	1.05	0.252	0.062	3.15	0.263	0.132	0.202	.	0.047	.	0.047	0.007	A
NCS HC16008b	3.45	1.84	0.046	0.018	1.44	0.015	0.019	A

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Ti	V	As	B	Cd	Ga	Pb	Sb	Sn	Tl	Units
GBW 01108b	3.45	1.84	0.046	0.018	1.44	0.015	0.019	A
ECRM 476-3	3.390	0.987	0.0908	0.0493	1.813	0.2445	0.0549	0.0648	.	.	0.0038	0.0222	0.0115	0.0145	A
CMSI 1504B	3.39	0.94	0.113	0.016	2.41	0.202	0.058	A
ECRM 487-1	3.27	0.094	0.0020	0.0007	0.0060	.	0.040	0.063	0.0088	.	0.0042	.	.	0.011	last	
NCS HC11009	3.26	1.98	0.385	0.081	1.18	0.020	.	0.373	.	.	.	0.024	0.0074	A
ECRM 492-1	3.258	.	.	0.0854	0.0048	A
ECRM 484-1	3.20	0.395	0.121	0.230	0.717	.	.	0.155	A
CMSI 1530	3.16	0.335	0.066	0.103	0.461	0.065	0.027	0.030	0.033	.	.	.	0.56	.	.	.	0.0078	.	.	last	0.225	
NCS HC28035	3.15	0.685	0.49	0.076	1.44	0.915	B
NCS HC30002	3.12	0.687	0.100	0.023	0.96	0.29	A
NCS HC28028	3.11	0.605	0.250	0.088	1.71	1.03	.	0.280	.	.	.	0.0494	0.023	B
NCS HC28012	3.06	0.77	0.071	0.094	1.36	0.068	0.0415	0.0325	.	.	.	0.032	B
NCS HC28014	3.05	0.57	0.300	0.079	2.67	0.194	0.018	0.022	B
GBW 01101B	3.04	1.22	0.072	0.052	1.34	0.025	0.008	A
CMSI 1501B	3.04	1.22	0.072	0.052	1.34	0.025	0.008	A
CMSI 1533	3.00	0.869	0.048	0.145	1.42	0.066	0.027	0.033	0.033	.	.	.	0.29	.	.	.	0.0077	.	.	.	0.254	A

* ERM 487-2 also contains: Al: 0.079, As: 0.0063, Te: 0.0064, and Zn: 0.0012

CAST IRON CHIPS WITH CARBON UNDER 3%

analysis listed in mass % except * which is mg/kg

unit sizes have been abbreviated as follows: A = 80 g, B = 100 g, C = 150 g, and D = 200 g

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Ti	V	As	B	Bi*	Ga*	Pb*	Sb*	Sn	Tl	Units
CRM																								
NCS HC28025	2.98	0.698	1.80	0.087	1.80	0.201	.	0.081	C
NCS HC39011	2.96	0.57	0.082	0.058	1.67	0.061	B
VS Ch1-1	2.94	0.271	0.0125	0.0290	0.293	0.101	0.061	0.051	0.046	B
NCS HC28026	2.90	0.702	1.91	0.124	1.81	0.245	.	0.086	C
ECRM 489-1	2.860	(0.510)	0.815	0.155	1.524	0.274	(0.0056)	B
NCS HC39013	2.86	0.56	0.106	0.052	2.35	0.0101	B
NCS HC28029	2.85	0.85	0.086	0.0995	1.91	0.865	.	0.316	0.033	0.017	C
VS Ch6/1	2.82	0.803	0.267	0.037	2.76	.	0.716	2.73	.	.	0.096	0.215	.	0.093	B
CMSI 1506A	2.809	1.48	0.039	0.062	0.856	0.045	0.0118	C
VS Ch4/7	2.78	0.742	0.194	0.0276	1.60	0.221	0.525	0.706	(0.006)	B
ECRM 428-2	2.747	0.750	0.0691	0.1105	1.751	0.0996	0.0358	0.0366	0.0311	0.0120	0.0156	B
GBW 01106b	2.71	0.98	0.077	0.089	1.14	0.036	.	0.089	0.007	B
NCS HC16006b	2.71	0.98	0.077	0.089	1.14	0.036	0.007	B
NCS HC11007	2.70	1.66	0.201	0.102	1.72	0.031	0.014	0.0067	B
NCS HC28013	2.65	0.575	0.450	0.098	2.29	0.086	0.0675	0.041	0.041	C
VS Ch16/1	2.64	1.23	0.0237	0.049	0.864	0.242	4.15	1.77	(0.007)	B
NCS HC41010	2.64	0.540	0.086	0.029	1.49	0.056	0.030	0.086	.	.	.	0.021	.	0.024	0.011	C
NCS HC41011	2.64	0.725	0.177	0.033	2.23	0.146	0.035	0.151	.	.	.	0.105	.	0.031	0.014	C
SRM 5m	2.59	0.74	0.32	0.133	1.83	0.89	0.041	0.080	.	.	.	(0.029)	(0.006)	(0.097)	0.033	C
NCS HC41012	2.52	1.24	0.635	0.032	3.86	0.114	0.037	0.115	0.017	0.071	0.033	8	11	.	.	C
VS Ch20	2.41	1.84	1.46	0.053	0.594	0.050	0.157	0.170	0.0040	(0.015)	0.089	B
CMSI 1534	2.38	1.28	0.069	0.077	2.12	0.070	0.028	0.030	.	.	0.034	.	.	.	0.40	.	.	.	73	.	.	.	0.314	B
GBW 01102b	2.38	0.700	0.082	0.034	0.48	0.026	0.006	B
CMSI 1502B	2.38	0.700	0.082	0.034	0.48	0.026	0.006	C
GBW 01109b	2.31	0.509	0.025	0.100	0.28	0.038	0.030	B
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Ti	V	As	B	Bi*	Ga*	Pb*	Sb*	Sn	Tl	Units
NCS HC16009b	2.31	0.509	0.025	0.100	0.28	0.038	0.030	B
VS Ch7/9	2.30	1.04	0.590	0.0154	2.67	.	.	0.130	0.590	(0.001)	B
NCS HC37032	2.28	0.358	0.086	0.161	1.34	0.041	.	0.028	B
VS Ch3/7	2.27	1.88	1.33	0.041	0.778	0.0013	B
NCS HC30001	2.26	1.28	0.178	0.025	2.21	1.01	B
NCS HC37030	2.22	0.869	0.339	0.101	2.20	0.501	.	0.142	B
NCS HC37041	2.22	0.869	0.339	0.101	2.20	0.501	.	0.142	B
ECRM 486-1	2.21	0.841	1.00	0.023	2.43	0.548	0.057	0.104	0.020	0.074	B
CMSI 1509A	2.202	0.528	0.0226	0.080	0.378	0.063	0.0094	C
NCS HC37029	2.15	1.08	0.451	0.068	2.69	0.752	.	0.221	B
NCS HC37040	2.15	1.08	0.451	0.068	2.69	0.752	.	0.221	B
BCS 170/4 *	2.15	0.78	0.70	0.080	2.45	0.60	B
CTIF FB20	2.114	0.464	0.039	0.128	1.012	.	.	0.035	B
NCS HC37013	2.11	0.353	0.167	0.139	1.70	.	.	0.119	25	A
IPT 49	2.11	0.272	0.012	0.019	0.78	0.040	0.021	0.020	A
NCS HC37028	2.04	1.34	0.479	0.038	3.37	0.642	.	0.197	B
NCS HC37039	2.04	1.34	0.479	0.038	3.37	0.642	.	0.197	B
NCS HC37042	2.04	0.670	0.226	0.103	1.86	0.176	.	0.054	B
NCS HC37038	2.01	0.677	0.057	0.115	1.44	.	.	0.113	15	B
NCS HC11008	1.90	1.96	0.060	0.097	2.72	0.041	.	0.766	0.013	0.0075	B
NCS HC37037	1.90	0.780	0.110	0.055	2.34	.	.	0.024	38	B
NCS HC37036	1.67	1.05	0.085	0.024	1.90	.	.	0.055	34	B
RM																								
CKD 215 *	2.46	0.76	0.087	0.17	3.08	0.43	0.081	0.15	.	0.01	.	0.05	.	0.04	0.05	0.02	0.048	.	D
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Ti	V	As	B	Bi*	Ga*	Pb*	Sb*	Sn	Tl	Units

* Clearance Sale Item

CRM OTHER IRON BASE CHIPS AND POWDER^{75 g}

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Sn	Ti	V	W	As	B	Fe	O
IARM Fe5140H-18	0.37	0.93	0.014	0.022	0.187	0.253	0.266	0.67	0.13	0.0081	0.031	0.007	(0.0015)	0.0069	0.0015	(0.0024)	(0.003)	(0.011)	.	.	.
IARM FeA100-18	0.222	(0.013)	(0.004)	(<0.0010)	(0.039)	(0.010)	11.2	2.98	(0.007)	13.4	1.19	(0.0010)	(0.003)	.	(0.008)	(0.007)	(0.006)	.	.	.	(0.0009)
IARM Fe8620-18	0.211	0.857	0.012	0.026	0.23	0.197	0.446	0.536	0.0246	0.0085	0.197	0.007	(0.0014)	0.0090	0.0015	0.0061	(0.004)	0.009	.	.	.
IARM Fe4820-18	0.192	0.541	(0.011)	0.0018	0.26	0.167	3.51	0.144	0.022	0.0107	0.287	0.007	(0.002)	0.0089	(0.0011)	0.0015	(0.004)	(0.006)	.	.	(0.003)
IARM FeE9310-18	0.121	0.62	0.009	0.0128	0.256	0.158	3.07	1.09	0.036	0.009	0.086	0.0070	.	0.0072	.	0.0030	.	.	.	94.6	(0.0017)
IARM FeDP1080-18	0.110	1.88	0.014	(0.006)	0.11	0.042	0.554	0.554	(0.002)	0.069	0.445	(0.009)	0.014	(0.0064)	(0.0013)	(0.0043)	(0.030)	.	.	.	(0.0055)
IARM Fe91-18	0.099	0.453	0.015	(0.002)	0.27	0.041	0.187	8.24	(0.006)	0.013	0.94	0.046	0.070	(0.004)	(0.0021)	0.198	(0.003)	.	.	.	(0.003)
IARM FeP92-18	0.092	0.737	(0.005)	(0.005)	0.20	0.074	0.82	9.4	(0.005)	0.036	0.52	(0.0036)	0.096	(0.006)	(0.003)	0.188	1.97	.	0.0026	.	(0.013)
IARM Fe174PH-18	0.041	0.47	0.024	(<0.0040)	0.52	3.33	4.73	15.10	0.007	0.047	0.315	0.0436	0.285	0.008	.	0.051	0.015	.	.	.	0.0035
IARM FeKovar-18	0.024	0.26	(0.004)	(0.0055)	(0.09)	0.077	29.0	0.068	.	17.3	0.062	.	.	0.0021	.	.	(0.020)	.	.	53.3	.
IARM Fe2205-18	0.018	1.18	0.023	(0.0013)	0.46	0.208	5.57	22.6	(0.007)	0.104	3.20	0.17	(0.011)	(0.006)	(0.003)	0.063	0.024	.	.	.	(0.004)
IARM Fe316LP-18	(0.006)	1.56	(0.011)	0.0041	0.29	0.0031	13.9	17.9	(0.006)	(0.006)	2.81	(0.081)	.	.	.	(0.006)	(0.043)